

JOTUN Industri Drygolin Ultimat

Product description

Features and benefits

The product gives a UV resistant and water repellent surface with a long lasting colour and gloss durability. Dries quickly and can be handled once the water has been driven off.

JOTUN Industri Drygolin Ultimat in system with **JOTUN Industri grunning Visir** or **JOTUN Industri Opaque Primer** gives the best surface for further treatment with **DRYGOLIN Ultimat**, **DEMIDEKK Infinity**, **DEMIDEKK Ultimate** or **JOTAPROFF Fasadakryl**. Recommended system gives very long maintenance interval.

Recommended use

Developed for industrial application on cladding.

Treatment for cladding treated with primer and 1 coat JOTUN Industri Drygolin Ultimat

The cladding is mounted in accordance with the current norms and standards for carpentry. The substrate must be clean, sound and dry before further treatment.

When mounting:	Prime cut surface, end grains and other untreated wood with VISIR Oljegrunning 3-4 coats wet-on-wet. This is then applied 1 coat DRYGOLIN Ultimat .
Within 2 years after the cladding has been mounted:	Topcoat is recommended applied with 1 coat DRYGOLIN Ultimat within 2 years. Best results are achieved if the topcoat is applied immediately after the cladding is mounted.
Maintenance interval:	The cladding should be inspected annually, by the homeowner. It is the owners responsibility to repair any damages. The product will naturally be degraded by external influences. Maintenance intervals are influenced by local climatic conditions and repainting must be made when needed.
Maintenance must be performed using:	Wash the house with JOTUN 2-i-1 Husvask og soppfjerner / JOTUN 2-i-1 Husvask och mögeldesinfektion / JOTUN 2-i-1 Husvask/Træ- og Murrens when necessary. Before further treatment (apply additional paint), the cladding should be washed with JOTUN 2-i-1 Kraftvask og Soppfjerner . This is to ensure good adhesion for the next coat and long maintenance intervals. Further maintenance is recommended with DRYGOLIN Ultimat , but other outdoor paints from Jotun can also be used. Follow the instruction manual of the product you choose.
Maintenance repair:	Loose fibres to be removed down to bare wood. Prime bare wood, any damages and end grains immediately with 3-4 coats VISIR Oljegrunning , wet-on-wet. Apply DRYGOLIN Ultimat , DEMIDEKK Infinity , DEMIDEKK Ultimate or JOTAPROFF Fasadakryl as topcoat.

Comments

In case of poor adherence to knots: The nature of the substrate affects how well the treatment will adhere. Knots and hard glossy surfaces with higher content of resins, phenols and terpenes adversely affect the adhesion of paint. This may cause flaking. Flaking is treated by removing loose paint with steel brushing / scraping before re-painting the area.

Application methods, recommended use and technical specifications

See Technical Data Sheet / packaging for the recommended products regarding directions for use, drying times, spreading rate and film thickness etc.

Environmental labelling

Green Building Standards

The declared product meets the following requirements:

BREEAM® NOR (2016)

Mat 1.3: Product specific type III EPD (ISO 14025, ISO 21930, EN 15804) for Scandinavia.

Mat 01: The product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

BREEAM® NOR (2012)

Mat 1.3: Product specific type III EPD (ISO 14025, ISO 21930, EN 15804) for Scandinavia.

Mat 1.5: This product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

Additional certificates and approvals may be available on request.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

VOC for Ready-for-Use Mixture

EU limit value for the product (cat. A/d): 130 g/l. The product contains max 30 g/l VOC.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.

Treated surface/substrate type

Painted in colour

Colour name

NCS code

Production number

Paint work done by

Date

Signature