

Torlak Conseal

Product description

Type

This product is an alkali resistant, solvent based primer. Based on alkyd resin.

Features and benefits

Contains Zinc phosphate as active corrosion preventing pigments. Resistant against dry heat up to 120°C. Ideal as a primer on most substrates.

Recommended use

Ideal as primer for steel and aluminium structures where a fast-drying primer is required.

Product data

Packaging size	0.375 L, 0.75 L and 4 L
Colours	White, grey and red
Solids	44 ± 2 volume%
Flash point	Closed cup: 37°C (98,6°F)
VOC	500 g/l ISO 11890 EU

Application data

Remarks

Handle with care. Stir well before use.

The product can be applied by

Roller : Recommended.

Brush : Recommended.

Spray : Use airless spray or conventional spray.

Guiding data for airless spray

Nozzle tip	0.38-0.53 mm (0.015-0.021")
Spray angle degrees	40° - 80°
Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi)

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Spreading rate per coat

Theoretical	Minimum	11 m ² /l	Maximum	7,3 m ² /l	Typical	8,8 m ² /l
-------------	---------	----------------------	---------	-----------------------	---------	-----------------------

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Recommended film thickness per coat

Wet	Minimum	90 µm	Maximum	135 µm	Typical	115 µm
Dry	Minimum	40 µm	Maximum	60 µm	Typical	50 µm

Film thickness will vary and is calculated as average.

Thinner

Jotun Thinner No. 7

Dilution

Maximum 10 %

Cleaning of painting tools

Jotun Thinner No. 2

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Relative Humidity (RH) 50 %

Substrate temperature	5 °C	10 °C	23 °C	40 °C
Surface (touch) dry	30 min	20 min	15 min	10 min
Hard dry	2.5 h	2 h	1.5 h	1 h
Dry to over coat, minimum	2.5 h	2 h	1.5 h	1 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Bare steel

Power tool cleaning to St 2 (ISO 8501-1)
Sa 2½ (ISO 8501-1)

Recommended paint system

Primer

Torlak Conseal : 1 Coat(s)

Topcoat

Torlak Classic Aluminio or Torlak Classic Brillante or Torlak Classic Mate or Torlak Classic Satinado : 2 Coat(s)

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.