

JOTAPROFF PVA 07

Product description

Type

Solvent free waterborne dispersion paint for use indoors in dry rooms.



Recommended use

Intermediate and topcoat on walls such as plaster, concrete, putty, boards, woven fabric, wallpaper etc, in dry rooms. **JOTAPROFF PVA 07** can be used as primer on unpainted wallboards and filler.

23° C-50% R.H. 23° C-50% R.H.



Overmalbar
Overmålningsbar
Dry to recoat



Min. air and
surface temp.



Vann/JOTUN Penselrens

Product data

Packaging size

3 L (filling level 2.7 L) and 10 L (filling level 9 L)

Base availability

White, A, B and C
Bases must not be used unless tinted.

Tinting

Bases must be tinted using **Jotun Multicolor**. Up to 10 % with **Jotun Multicolor** colorants.

If white base is bought as white colour, it shall NOT be tinted using **Jotun Multicolor**.

All other colour formulations to be mixed over **Jotun Multicolor**.

Colours

White base is a fully pigmented white color.
NCS 0500-N, NCS 0502-Y.

Gloss level

Silky matt 07

Glansgradtabell for JOTAPROFF PVA



Generic type

PVA copolymer dispersion panit

Solids by volume

40 ± 2 volume%

Specific gravity

1.4

VOC for Ready-for-Use Mixture

EU limit value for the product (cat. A/a): 30 g/l. The product contains max 1 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed to avoid possible colour deviations. Stir well before use.

Application equipment / methods

Roller, brush or spray. Preferred application with roller, but brush or airless spray may also be used. Apply rich and evenly.

Guiding data for airless spray

Nozzle tip	0.43-0.53 mm (0.017-0.021")
Spray angle degrees	50-80°
Pressure at nozzle	Min. 15 MPa (Min. 150 kg/cm ²)

Cleaning of painting tools

Water and **JOTUN Penselrens** or water and a suitable cleaning agent.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	8 - 10	100 - 125	40 - 57

Conditions during application

Temperature of substrate and air must be minimum +10 °C.

Cleaning of spillage

JOTUN Spezial wipen are recommended to clean spillage. **JOTUN Spezial wipen** are a convenient washing/cleansing wipe for use before and during paint work.

Drying times

Drying times deviate because of changes in temperature, air humidity, air circulation and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C
Surface (touch) dry	Ca 1 h
Recoatable, minimum	2 h
Dry to use	Ca 24 h
Fully cured	4 weeks

Directions for use

The substrate must be clean, sound and dry.
Clean with **JOTUN Spesialvask før maling**.
Bare iron and nail heads to be primed with **QUICK Bengalack Grunning** or a suitable primer.

Substrate	Treatment
Unpainted absorbent substrates:	Unpainted absorbent substrates, like wallpaper and unpainted concrete/plastered walls, must be primed before applying middle coat and topcoat. Topcoat: 2 x JOTAPROFF PVA 07 . On absorbant, porous surfaces 3 coats are recommended to avoid discolouring.
Previously painted:	Sand down previously painted old glossy/semi glossy paint with suitable abrasive paper and remove dust. Old glossy/semi glossy paint must be primed with JOTUN Heftgrunning Universal . Topcoat: 2 x JOTAPROFF PVA 07 . On absorbant, porous surfaces 3 coats are recommended to avoid discolouring.
Ceilings discoloured by soot, nicotine etc.:	Prime with JOTUN Kvist- og sperregrunning . Topcoat: 2 x JOTAPROFF PVA 07 . On absorbant, porous surfaces 3 coats are recommended to avoid discolouring.

Maintenance

Newly painted surfaces must not be cleaned the first four weeks (the product's curing time).
If cleaning is necessary, the pH of the detergent must not exceed pH 9.
JOTUN Spesialvask før maling is recommended.
For daily cleaning the temperature of the wash water must be <40 °C.

Storage

In storage and in transport keep the container frost free and upright.
The quality of a tinted product will reduce when stored more than one year.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Green Building Standards

The declared product meets the following requirements:

- The emission requirements for M1: Classification of Indoor Environment 2018
- Swan (2096 0002)
- Property criteria in BASTA (2016:A1)
- Accepted according to Building Evaluation Assessment Criteria (Byggvarubedömningens Bedömningskriterier) 4.0 (2016)
- Class B according to Bedömningskriterier (Assessment Criteria) 6.0 for SundaHus (2013)

The declared product contributes to Green Building Standard credits by meeting the following specific requirements:

- BREEAM® International v6.0 (2021)/BREEAM® International (2016)
- Hea 02: VOC exemplary emission (ISO 16000-series) and the VOC content for Interior matt walls and ceilings (Gloss <25@60°) (10 g/l).
 - Mat 01: Product-specific Type III EPD (ISO 14025;21930, EN 15804+A2) for Jotun A/S.

- BREEAM-NOR v6.0 (2022)
- Hea 02-02: Pattern valid level. VOC content for "Matt indoor wall and ceiling paint" (10 g/l) and emission requirements (ISO 16000 series).
 - Mat 02: Product-specific Type III EPD (ISO 14025, ISO 21930, EN 15804+A2) for Jotun A/S.
 - Mat 02: The product's safety data sheet confirms that the product does not contain any substances on the Norwegian priority list (A20 list) and REACH approval/authorisation list – Annex XIV, prohibitions and restrictions – Annex XVII and SVHC candidate list.

- BREEAM® NOR (2016)
- Hea 02: VOC content for "Matt indoor wall and ceiling paint" (30 g/l) (EU Directive 2004/42/CE) and emission requirements (ISO 16000 series).
 - Mat 01: Product specific type III EPD (ISO 14025, ISO 21930, EN 15804) for Jotun A/S.
 - Mat 01: The product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

Additional certificates and approvals may be available on request.
The EPDs are available at www.epd-norge.no

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.
Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Indoor environment / Emission

The product gives low emission which is measured on a neutral substrate. Substrate and preparation prior to treatment will have an influence on the total emission from finished surface.

Contact information

Norway Coatings B.V.
Vaalmuiden 9
1046 BV AMSTERDAM
T: 088 450 5400
www.norwaycoatings.nl

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.