

Wood Barniz Brillante

Product description

Type

This product is a high performance coating formulated with urethane synthetic resins and is gloss finish.

Features and benefits

High penetration in the surface. Strong and hard finish. Contains UV filter, which protects the wood against discolouration and fading caused by light.

Recommended use

Ideal for any kind of surfaces, both in interiors and exteriors, including parquet.

Substrate

Wood.

Product data

Packaging size 0.375 L, 0.75 L and 4 L

Solids by volume 38 \pm 2 volume% Theoretical

Application data

The product can be applied by

Roller: Recommended.
Brush: Recommended.

Gun: Airless spray may be used.

Film thickness per coat

Typical recommended range

Dry film thickness 30 - 40 μm Wet film thickness 80 - 105 μm

Film thickness will vary and is calculated as average.

Theoretical spreading rate 12.7 - 9.5 m²/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Dilution

Ready to use.

Conditions during application

The temperature of the substrate should be minimum 10 $^{\circ}$ C and at least 3 $^{\circ}$ C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 $^{\circ}$ C (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Date of issue: 29.11.2021 Product code: 1363 Page: 1/3

Technical Data Sheet Wood Barniz Brillante



Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- 1. Recommended data given is, for recoating with the same generic type of paint.
- 2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
- 3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values: Relative Humidity (RH) 50 % Substrate temperature	10 °C	23 °C	40 °C
Hard dry	48 h	24 h	18 h
Dry to over coat, minimum	24 h	12 h	8 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Topcoat

Jotun Wood Impregnacion Protectora: 1 Coat

Wood Barniz Brillante: 2-3 Coats

In order to achieve a very smooth finish, it is recommended to sand between coats.

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Wood Barniz Brillante

48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Date of issue: 29.11.2021 Product code: 1363 Page: 2/3

Technical Data Sheet Wood Barniz Brillante



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4. **Handling and storage**, refer to section 7. **Transport information**, refer to section 14. **Regulatory information**, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

Date of issue: 29.11.2021 Product code: 1363 Page: 3/3