

JOTUN Industri Terrassebeis

Product description

Type

Oil based, water soluble stain. Based on the same technology as **TREBITT Terrassebeis**.

Features and benefits

Has good penetrating ability and gives a good protection against decay caused by UV light and fungus attack. The product gives the decking panels a water repellent effect. Contains pigments and light filters that protect the wood against decay caused by UV light. Contains effective film conserving agent that counteract mould growth. This gives maintenance intervals up to three years.

Recommended use

For industrial treatment of decking panels. Recommended for use on impregnated decking panels where a transparent, non-filmforming protection of the wood is required.

Substrate

The substrate must be clean, sound and dry: Maximum humidity content in the wood 18 % Surface and air temperature must be minimum +15 °C. The product has less penetration into and around the knots. Wear, gloss and color differences may occur as a result.

Product data

Packaging size	18 L
Base availability	C-base
Tinting	Bases must be tinted using Jotun Multicolor .
Colors	Colours and color nuances are very important in translucent systems. The substrate might influence the end result. A wrong colour choice of a translucent stain is difficult to correct. Set a test patch before work starts.
Generic type	Alkyd emulsion.
Solids by volume	36 ± 2 volume%
Specific gravity	1.01
pH value	8.6
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/e): 130 g/l. The product contains max 10 g/l VOC.

Application data

Remarks

The product is designed for industrial application. Apply thinly and must not form film. Remove excess stain.

Application equipment / methods

Industrial application using brush machine.

Cleaning of painting tools

Machinery and equipment must be cleaned with water.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Recommended film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
	15 - 22	45 - 67	16 - 24

Thinner

Water

Can be diluted with water up to 40 %. The applied wet film thickness must be compensated for when diluting.

Conditions during application

Temperature of air and substrate must be above +15 °C during painting. Moisture content of woodwork max 18%.

Drying times

Water must be driven off before stacking/packing.

Dry to use 24 h

Directions for use

Remarks

Contact your local Jotun representative for guidance and testing.

Maintenance

Storage

Frost free freight and storage.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.