

Woodshield Stain Interior Matt

Product description

Туре

This product is based on a superior quality modified urethane alkyd resin, which provides high quality wood finishes.

Features and benefits

Durable Stain which gives outstanding gloss & colour retention and weather resistance. Low odour and water resistant. Free from harmful heavy metals such as Mercury, Lead, Cadmium, Arsenic, Chromium etc.

Recommended use

Ideal for all kinds of interior untreated hardwood, softwood, plywood, chip board etc. Can also be used as a topcoat for an anti termite and fungal system with Jotun Wood Preserver as undercoat.

Substrate

Wood

Product data

Packaging size	1 L and 4 L Egypt and Libya : 1 L and 3 L
Solids by volume	37 ± 2 volume% Theoretical
Specific gravity	0.9 Theoretical
VOC	479 g/l ISO 11890 EU
VOC comments	This is the theoretical value. Tested value will vary depending on test methodology, accuracy of equipment used for testing and test conditions.

Application data

The product can be applied by

Roller : Recommended. Spray : Use conventional spray. Brush : Recommended.

Cleaning of painting tools

Jotun Thinner No. 2

Film thickness per coat

Typical recommended range

Dry film thickness	25	-	35	μm	
Wet film thickness	70	-	97	μm	
Film thickness will vary and is calculated as average.					
Theoretical spreading rate	15.1	-	10.5	m²/l	

Date of issue: 05.01.2023

Product code: 16643

Page: 1/3

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.

Technical Data Sheet Woodshield Stain Interior Matt



Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Thinner

Jotun Thinner No. 2

Dilution

Maximum 10 %

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the substrate should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1.Recommended data given is, for recoating with the same generic type of paint.

2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.

3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

10 °C	23 °C	40 °C
4 h	2 h	1 h
8 h	2 h	3 h
8 h	4 h	3 h
	4 h 8 h	4 h 2 h 8 h 2 h

Directions for use

Surface preparation

The substrate must be clean and dry. Surface contamination is to be removed by thoroughly rubbing down in the direction of the wood grain, using a suitable abrasive paper and dusted off.

Recommended paint system

Topcoat

Woodshield Stain Interior Matt : 1 - 2 Coat(s)

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

This product is available in: United Arab Emirates, Bahrain, Kuwait, Qatar, Saudi, Oman, Egypt and Libya

Product code: 16643

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.



Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Certificates

Inductively coupled plasma - Atomic emission spectrometry (ICP-AES) : No traces of Arsenic(As), Chromium(Cr), Cadmium(Cd), Mercury(Hg) and Lead(Pb) were found. : **TÜV SÜD PSB Pte Ltd.**

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet. **First-aid measures**, refer to section 4. **Handling and storage**, refer to section 7. **Transport information**, refer to section 14. **Regulatory information**, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

Date of issue: 05.01.2023

Product code:

e: 16643

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.