Technical Data Sheet



DRYGOLIN Ultimat

Product description

Туре

Oil based paint based on modern hybrid technology with a high quantity of alkyd oil.

Features and benefits

An outdoor modern oil based paint with a particularly long shelf life. The paint has very good protection against the harsh and varied Norwegian weather and has long-lasting color and gloss durability. Contains effective film conserving agent that counteracts the risk of black mold growing on the wood surface. The coating has excellent application properties and and is fast-drying - 2 coats in one day.

Recommended use

To be applied to new, previously stained or painted woodwork, as well as impregnated. Also suitable as a topcoat for previously primed gutters, fascia's made of plastic and metal commonly use on buildings.











Product data

Packaging size	3 L (filling level 2.7 L) and 10 L (filling level 9 L) pail		
Base availability	A, B, C, ochre, oxide red and yellow. Bases must not be used unless tinted.		
Tinting	Bases must be tinted using Jotun Multicolor .		
Colors	White		
Gloss level	45-55 semi gloss		
Generic type	Oil based paint based on modern hybrid technology with a high quantity of alkyd oil.		
Solids by volume	37 ± 2 volume% (white)		
Specific gravity	1.28 (white)		
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 80 g/ l VOC.		

Application data

Remarks

To ensure long durability it is important to apply a sufficient amount on edges and planed surfaces, min. 3 coats (100 μ m dry paint film). Sand down sharp edges. Remember to coat end grain. Perform a test application. Can not be mixed with other paint products and do not mix in oil additives. The product is water soluble. The product shall not be thinned.

Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Linseed oil / oils in the substrate can cause blisters and flaking. Sun on semi-dry paint may cause skin drying and sun blisters. Painting on fire protected cladding may cause salt precipitation/flaking.

Date of issue:

10.01.2022

Product code: 19920

Product family:

19C

Page: 1/4

This technical data sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.





Bases must be tinted using **Jotun Multicolor**. Content of cans from different productions and different tinting systems may cause shade differences. Measures one can take to avoid colour differences:

- Mix different production numbers together. Stir well. The production number can be found after the letters SZ or SV on the label in the front of the can.
- It is advantageous to use the same batch number within the same defined area. Changing the can in the middle of the wall or confined area, increases the possibility of a visible colour difference.
- There may be colour differences of paint which are mixed on different tinting machines and / or at different times. Please be aware of this if you need to buy more paint / opaque stain / stain for the same project at a later time.
- If you notice any visible differences, contact your point of sale or Jotun Technical Service (tel. 33457530).

Application equipment / methods

Brush, roller or spray.

Guiding data for airless spray

Nozzle tip	0.46 mm (0.018")		
Spray angle degrees	65-80°		
Pressure at nozzle	15–18 MPa (150–180 kg/cm²)		

Spreading rate and film thickness

	Spreading rate per coat	Film thickness per coat (µm)		
	(m²/liter)	Wet (calculated)	Dry (calculated)	
Recommended, sawn wood:	6 - 8	125 - 167	46 - 62	
Recommended, planed wood:	8 - 12	83 - 125	31 - 46	

Comments:

To ensure long durability it is important to apply a sufficient amount on edges and planed surfaces, min. 3 coats (100 μm dry paint film).

Dilution

Can not be mixed with other paint products. Do not mix in oil additives.

Conditions during application

Air and surface temperature must be above +5 °C during application.

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

- High humidity (RH%) significantly prolongs the drying time for waterborne products.
- Warm air can hold more moisture than cold air, and in case of temperature drop this can cause condensation.
- Stagnant air retards the drying, and can provide greater risk of condensation.
- Low temperature and condensation can provide inadequate film formation / curing.

Where condensation is possible, one should therefore finish the painting job well in advance.

Cleaning of painting tools

Water and JOTUN Penselrens.

Product family:

19C

This technical data sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.

19920



Drying times

Drying times deviate because of changes in temperature, air humidity, wind, absorption and film thickness. Lower temperature will extend the drying times.

The drying time is measured by stated values:						
Relative Humidity (RH)	50 %	50 %	50 %			
Air temperature	5 °C	15 °C	23 °C			
Substrate temperature	5 °C	15 °C	23 °C			
Dust dry	6 h	4 h	2 h			
Recoatable, minimum	12 h	6 h	4 h			

Directions for use

The substrate shall be firm, clean and dry. For the best possible edge coverage, sand down sharp edges.

Substrate	Treatment
New woodwork:	Before or immediately after installation of new woodwork, treat with a brush coat of VISIR Oljegrunning . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: DRYGOLIN Ultimat . New, planed woodwork: 3 coats. New, sawn wood: 2 coats.
Fresh wood left untreated for more than 4 weeks:	Should be cleaned using JOTUN 2-i-1 Husvask og soppfjerner / JOTUN 2-i-1 Husvask och mögeldesinfektion / JOTUN 2-i-1 Husvask/Træ- og Murrens and brushed with a wire brush. Apply VISIR Oljegrunning to bare woodwork. The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: DRYGOLIN Ultimat . New, planed woodwork: 3 coats. New, sawn wood: 2 coats.
Previously treated wood:	Should be cleaned using JOTUN 2-i-1 Kraftvask og soppfjerner / JOTUN 2-i-1 Kraftvask och mögeldesinfektion / JOTUN 2-i-1 Husvask/Træ- og Murrens and brushed with a wire brush. Remove loose paint/stain and wood fibers by wire brush or scraping. Sand glossy and hard surfaces. Bare spots (from drybrushing/scraping) to be primed with VISIR Oljegrunning. The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: 2 coats DRYGOLIN Ultimat. Primed spots: 1–2 coats followed by 2 full coats.
Gutters, fascias made of plastic and metal commonly used on buildings:	Clean with JOTUN 2-i-1 Kraftvask og soppfjerner / JOTUN 2-i-1 Kraftvask och mögeldesinfektion / JOTUN 2-i-1 Kraftvask/Træ- og Murrens. Prime the metal with QUICK Bengalack Grunning. Apply 2 coats DRYGOLIN Ultimat.

Maintenance

We recommend to wash the house using JOTUN 2-i-1 Husvask og soppfjerner / JOTUN 2-i-1 Husvask och mögeldesinfektion / JOTUN 2-i-1 Husvask/Træ- og Murrens if necessary.

Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Date of issue:

10.01.2022

Product code: 19920

Product family:

19C

Page: 3/4

This technical data sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.



Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet. **First-aid measures**, refer to section 4. **Handling and storage**, refer to section 7. **Transport information**, refer to section 14. **Regulatory information**, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

45941473, 45941484, 45942566, 45949604, 45942816, 45949642, 45942585, 45949612, 45942733, 45949623, 45949657, 45949661, 45942763, 45949638

NOBB module number

41871553

Contact information

Jotun A/S P.O.Box 2021 3202 Sandefjord Tel: 33 45 70 00

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.

Date of issue: 10.0

10.01.2022

Product code: 19920

Product family:

19C

Page: 4/4

This technical data sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.