

Tankguard 412 T

Product description

This is a two component solvent free polyamine cured epoxy coating. Specially designed as a HB variant of standard Tankguard 412 to achieve high DFT (upto 800 mic) in single coat application by automatic spray line. Specially designed as a HB variant of standard Tankguard 412 to achieve high DFT (upto 800 mic) in single coat application by automatic spray line. It is a general purpose tank and pipe lining with good chemical resistance. Can be used as primer, mid coat or finish coat in atmospheric and immersed environments.

Typical use

Marine:

Can be used as a coating for potable water, grey water and crude oil tanks.

Protective:

Recommended as an internal lining for offshore, onshore and buried tanks and pipes. Refer to Protective Product Resistance List. Recommended for offshore environments, including splash zones, refineries, power plants, bridges, buildings, mining equipment and general structural steel.

Colours

white, red

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	98 ± 2 %
Gloss level (GU 60 °)	ISO 2813	gloss (70-85)
Flash point	ISO 3679 Method 1	100 °C
Density	calculated	1.5 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested) (CARB(SCM)2007, SCAQMD rule 1113, Hong Kong)	90 g/l
VOC-EU	IED (2010/75/EU) (theoretical)	140 g/l
VOC-EU	EU VOC Directive 2004/42/CE (theoretical)	140 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Gloss description: According to Jotun Performance Coatings' definition.

The VOC values refer to white colour.

Film thickness per coat

Typical recommended specification range

Dry film thickness	500 - 800 µm
Wet film thickness	500 - 800 µm
Theoretical spreading rate	2 - 1.25 m ² /l

Horizontal surfaces can be applied up to 1000 µm per coat.

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Stainless steel	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface.	Abrasive blast cleaning to achieve a surface profile using non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Galvanised steel	The surface shall be clean, dry and appear with a rough and dull profile.	Sweep blast-cleaning using non-metallic abrasive leaving a clean, rough and even pattern.
Concrete	Dry abrasive blast cleaning to SSPC-SP 13/NACE No. 6.	Dry abrasive blast cleaning to SSPC-SP 13/NACE No. 6.

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

Application

Application methods

The product can be applied by

Spray:	Use airless spray.
Brush:	Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

Tankguard 412 T Comp A	2 part(s)
Tankguard 412 Comp B	1 part(s)

Thinner/Cleaning solvent

Prior to application in potable water tanks flush the application equipment with Jotun Thinner No. 28. Use Jotun Thinner No. 17 for cleaning equipment after application.

Guiding data for airless spray

Nozzle tip (inch/1000):	21-35
Pressure at nozzle (minimum):	175 bar/2500 psi

Drying and Curing time

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	15 h	6 h	1.5 h
Walk-on-dry	30 h	12 h	4 h
Dry to over coat, minimum	30 h	12 h	4 h
Dried/cured for service	15 d	7 d	4 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 60 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Induction time	10 min
Pot life	1 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C
Immersed, sea water	50 °C	60 °C
Immersed, crude oil	70 °C	80 °C

Further resistance information can be found in Protective Product Resistance List available on Jotun's website, or contact your local Jotun office.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy
Subsequent coat: epoxy

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Tankguard 412 T Comp A	10	20
Tankguard 412 Comp B	5	5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Tankguard 412 T Comp A 12 month(s)
Tankguard 412 Comp B 12 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.