

LADY Supreme Finish halvblank (2011-2021)

Product description

Type

Water-borne oil paint for woodwork indoors.

Features and benefits

Provides an even, strong and smooth surface with an elegant appearance. It has low odour.

Recommended use

Middle and Topcoat on panels, MDF, furniture, doors, trimmings and moldings.

Product data

Packaging size	According to the current price list.
Base availability	White, A, B and C
Tinting	Bases must be tinted using Jotun Multicolor. Up to 10 % with Jotun Multicolor colorants.
Colours	White base may be used untinted as White.
Gloss level	40 semi gloss
Generic type	Water-borne polyurethane modified oil paint.
Solids	36 ± 2 volume%
Specific gravity	1,1 - 1,3
VOC for Ready-for-Use Mixture	EU limit value for this product (cat. A/d): 130 g/l. This product contains max 89 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed. Stir well. Oil paint may turn yellow over time.

Application methods

Brush or roller and brush. Apply rich and evenly.

Guiding data for airless spray

Nozzle tip	0.53 mm (0.021")
Spray angle degrees	65°-80°
Pressure at nozzle	15 MPa (150 kg/cm ²)

The product must only be sprayed by professional users.

Cleaning of painting tools

Water and a suitable cleaning agent.

Spreading rate per coat

Recommended 8 m²/l - 10 m²/l

Recommended film thickness per coat

Wet (calculated)

Recommended 100 µm - 125 µm

Dry (calculated)

Recommended 36 µm - 45 µm

Thinner

The product is ready to use and should not be thinned.

Conditions during application

Air and surface temperature must be above +10 °C during application.

Drying times

Relative Humidity (RH) 50 %

Air temperature	23 °C
Substrate temperature	23 °C
Surface (touch) dry	2 h
Repaintable after	8 h
Dry to use	24 h
Fully cured	4 weeks

Directions for use

Surface preparation

The substrate must be clean, sound and dry.

Untreated yellowed paneling must be cleaned with JOTUN Spesialrens gulnet panel, 1:10. Sand lightly and remove the dust.

Previously painted wood: Clean with JOTUN Spesialvask før maling. Use gloves. Sand down and remove dust.

MDF and hard, smooth surfaces: Sand down and remove dust.

Primer

Unpainted woodwork: 1-2 x JOTUN Kvist- og sperregrunning.

MDF and hard, smooth surfaces: 1 x JOTUN Heftgrunning Universal.

Topcoat

2 x LADY Supreme Finish halvblank. Light sanding between coats is recommended for best end result.

Cleaning of spillage

JOTUN Spesial wipes is recommended to clean spillage. JOTUN Special wipes is a convenient washing/cleansing wipe for use before and during paint work.

Maintenance

Newly painted surfaces must not be cleaned the first four weeks (the product's curing time). If cleaning is necessary, the pH value must not be above pH9. "JOTUN Spesialvask før maling" is recommended. For daily cleaning the suds temperature must be <40 °C.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Environmental labelling



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: Under declaration

1-1 **1993**

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.