

JOTAPROFF Akryl 10

Product description

Type

Solvent free water-borne acrylic dispersion paint.

Features and benefits

Silky matt Has high mechanical durability. Very good adhesion to the surface.

Recommended use

For interior application. Use for intermediate coats and top coats where a silk matt surface is desired.

Substrate

For walls on substrates such as boards, overpaintable wallpaper, woven fabric, plaster, concrete and putty.

Product data

Packaging size	3 L (content 2.7 L) and 10 L (content 9 L)
Base availability	White, A, B, C and yellow.
Tinting	Bases must be tinted using Jotun Multicolor . If white base is bought as white colour, it shall NOT be tinted using Jotun Multicolor . All other colour formulations to be mixed over Jotun Multicolor . Up to 10 % with Jotun Multicolor colorants.
Colors	White base is a fully pigmented white color.
Gloss level	Silky matt 10
Generic type	Water-borne acrylic paint.
Solids by volume	42 ± 2 volume%
Specific gravity	1.38
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/a): 30 g/l. The product contains max 1 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed. Stir well.

Application equipment / methods

Brush, roller or spray. Preferred application with roller, but brush or airless spray may also be used. Apply rich and evenly.

Guiding data for airless spray

Nozzle tip	0.53 mm (0.021")
Spray angle degrees	65–80°
Pressure at nozzle	Min. 15 MPa (Min. 150 kg/cm ²)

Cleaning of painting tools

Water and **JOTUN Penselrens**.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Recommended film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	7 - 10	100 - 143	42 - 60

Conditions during application

Temperature of substrate and air must be minimum +10 °C.

Drying times

Drying time deviates at changes in temperature, air humidity, air circulation and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Air temperature 23 °C

Substrate temperature 23 °C

Dust dry 1 h

Paintable 3 h

Dry to use 24 h

Directions for use

Surface preparation

The substrate must be clean, sound and dry: Clean with **JOTUN Spesialvask før maling**.

Sand down previously painted, old glossy/semi glossy paint with suitable abrasive paper and remove dust.

Pretreatment

Bare iron and nail heads to be primed with **QUICK Bengalack Metallgrunning**.

Primer

Unpainted absorbent substrates, like wallpaper and unpainted concrete/plastered walls, must be primed before applying middle coat and topcoat.

Previously painted: Old glossy/semi glossy paint must be primed with **JOTUN Heftgrunning Universal**.

Ceilings discoloured by soot, nicotine etc.: Prime with **JOTUN Kvist- og sperregrunning**.

Topcoat

2 x **JOTAPROFF Akryl 10**. 3 coats on absorbant, porous surfaces is recommended to avoid discolouring.

Cleaning of spillage

JOTUN Spezial wipes is recommended to clean spillage. **JOTUN Spezial wipes** is a convenient washing/cleansing wipe for use before and during paint work.

Maintenance

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.