

JOTUN Vegg og tak

Product description

Type

Water soluble, solvent free combination paint, containing acrylic, for use indoors.

Recommended use

Middle and topcoat on walls such as plaster, concrete, putty, boards, woven fabric, wallpaper etc, in dry rooms.

Product data

Packaging size	3 L (BASE 2.7 L) and 10 L (BASE 9 L)
Base availability	White/A, B and C
Tinting	Must be tinted using Jotun Multicolor. Up to 10 % with Jotun Multicolor colorants.
Gloss level	Matt 05
Generic type	PVA dispersion paint, containing acrylic.
Solids	38 ± 2 volume%
Specific gravity	1,5
VOC for Ready-for-Use Mixture	EU limit value for this product (cat. A/a): 30 g/l. This product contains max 1 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed to avoid possible colour deviations. Stir well.

Application methods

Preferred application with roller, but brush or airless spray may also be used. Apply rich and evenly.

Guiding data for airless spray

Nozzle tip	0.46-0.53 mm (0.018-0.021")
Spray angle degrees	65°-80°
Pressure at nozzle	Min. 15 MPa (Min. 150 kg/cm ²)

Cleaning of painting tools

Water and a suitable cleaning agent.

Spreading rate per coat

Recommended 7 m²/l - 10 m²/l

Recommended film thickness per coat

Wet (calculated)

Recommended 100 µm - 143 µm

Dry (calculated)

Recommended 38 µm - 54 µm

Conditions during application

Surface and air temperature must be minimum +10 °C.

Drying times

Drying time deviates at changes in temperature, air humidity, air circulation and film thickness.

Relative Humidity (RH) 50 %

Air temperature 23 °C

Substrate temperature 23 °C

Surface (touch) dry 30 min.

Repaintable after 1 h

Dry to use 24 h

Fully cured 4 weeks

Directions for use

Surface preparation

The substrate must be clean, sound and dry: Clean with JOTUN Spesialvask før maling. Sand down previously painted, old glossy/semi glossy paint with suitable abrasive paper and remove dust.

Pretreatment

Bare iron and nail heads to be primed with a suitable primer.

Primer

Chalking, bleeding and porous substrates: Should be brushed and then primed with JOTUN Heftgrunning Universal. Surfaces discoloured by soot, nicotine etc.: Prime with JOTUN Kvist- og sperregrunning.

Topcoat

2 coats JOTUN Vegg og tak.

Cleaning of spillage

JOTUN Spesial wipes is recommended to clean spillage. JOTUN Special wipes is a convenient washing/cleansing wipe for use before and during paint work.

Maintenance

Newly painted surfaces must not be cleaned the first four weeks (the product's curing time). If cleaning is necessary, the pH value must not be above pH9. "JOTUN Spesialvask før maling" is recommended. For daily cleaning the suds temperature must be <40 °C.

N/A

Storage


In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental labels Svanen (the swan) and the ECO label.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

N/A

48273237, 48273275, 48273218, 48273256, 48273222, 48273260

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.