

Jotun Ultra Primer

Product description

Type

A superior performance water-based primer that is specially formulated to provide excellent paint adhesion to extend the durability of premium paint systems and to tackle the common wall problems, such as peeling, flaking, efflorescence and spot discolouration caused by alkaline attack.

Features and benefits

Excellent paint adhesion

Offers excellent adhesion between concrete surfaces and topcoat to ensure long lasting paint performance. It can even be used on slightly chalking old concrete surfaces for repainting.

Anti-efflorescence & anti-discolouration

Prevents the formation of unsightly white powdery efflorescence on painted walls by sealing off the concrete surface. It also resists spot discolouration by blocking alkaline in new concrete from attacking the paint film.

Suitable for fresh concrete

It can be painted as the foundation of paint systems on freshly plastered concrete surfaces after 3 days of curing under good ventilation and weather condition, where moisture level of the fresh concrete is below 25% and pH below 11.

Water Resistant

Resist water ensuring less stain marks.

Formulated without Harmful Chemicals

Free from harmful chemicals such as APEO, formaldehyde, heavy metals and has low volatile organic compound (VOC).

Complies to Singapore Green Label

Recommended use

Suitable to be used on new and previously painted exterior and interior walls.

Substrate

On concrete and masonry surfaces.

Product data

Packaging size	Packing may vary from country to country according to local requirements.
Colours	White
Solids	32 ± 2 volume%

Application data

Remarks

Handle with care. Stir well before use.

Application methods

By brush, roller, airless spray or conventional spray.

Guiding data for airless spray

Nozzle tip	0.021" - 0.027"
Spray angle degrees	65° - 85°
Pressure at nozzle	140 - 190 kg/cm ² (2100 psi)

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Recommended film thickness per coat

Dry film thickness	: 30 - 40	microns μm
Wet film thickness	: 93.8 - 125	microns μm

Film thickness will vary and are calculated as an average.

Spreading rate per coat

Theoretical Spreading rate per coat (m²/l) : 8 - 10.7

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Thinner

Water

Dilution

The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 5%.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

1. Recommended data given is, for recoating with the same generic type of paint.

2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.

3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

Relative Humidity (RH)	50 %	50 %	50 %
Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	2 h	1 h	0.5 h
Hard dry	8 h	6 h	4 h
Dried to over coat, minimum	4 h	2 h	1 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of foam release agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Jotun Ultra Primer : 1 Coat(s)

Topcoat

Jotashield (New) series/Majestic series : 2 Coat(s)

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health- and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.