

## Jotashield ColourLast Matt (I)

### Product description

#### Type

This product is a superior quality, exterior, 100% pure acrylic water based topcoat.

#### Features and benefits

The unique UV protected colours offer outstanding protection against destructive effect of UV rays present in sunlight. The special acrylic binder provides durable and long lasting matt finish with low dirt pick up. Its unique formulation protects concrete from carbonation (Acts as anticarbonation coating). Resistant to algae and fungus.

#### Recommended use

Ideal for decorating and protecting exterior surfaces and specially suits as a maintenance product.

#### Substrate

Cement plaster, concrete, block work, rendered surfaces etc.

### Product data

<b>Packaging size</b>	1 L, 4 L, 10 L and 20 L
<b>Colours</b>	Refer to Jotashield exterior colour card.
<b>Solids by volume</b>	35 ± 2 volume% Theoretical
<b>VOC</b>	37 g/l ISO 11890 EU

### Application data

#### The product can be applied by

Spray : Use airless spray or conventional spray.

Roller : Recommended.

Brush : Recommended.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.021-0.027"
<b>Spray angle degrees</b>	65-80°
<b>Pressure at nozzle</b>	140 - 190 kg/cm <sup>2</sup> (2100 psi)

#### Cleaning of painting tools

Water

### Film thickness per coat

#### Typical recommended range

Dry film thickness 27 - 37  $\mu\text{m}$

Wet film thickness 70 - 87  $\mu\text{m}$

Film thickness will vary and is calculated as average.

Theoretical spreading rate 9.5 - 12.9  $\text{m}^2/\text{l}$

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

### Thinner

Water

### Dilution

30 %

### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

#### The drying time is measured by stated values:

##### Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	12 h	6 h	2 h
Hard dry	16 h	8 h	4 h
Dry to over coat, minimum	12 h	6 h	2 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

#### Primer

Jotashield Alkali Resistant Primer (I) or Acrylic Emulsion Primer (I) or Jotashield Penetrating Primer : 1 Coat

### Topcoat

Jotashield ColourLast Matt (I) : 2 Coats

### Remarks

Other systems may be specified, depending on area of use.

Masking tape has to be removed immediately after application of the topcoat.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

If any Block filler is used to rectify imperfections on the substrate, proper sanding followed by a full undiluted coat of Penetrating Sealer must be used before applying any Jotashield topcoats.  
This product is available in: India

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.