

## Hardtop Eco

### Product description

This is a two component chemically curing aliphatic acrylic polyurethane coating. It has a glossy finish with very good gloss retention. It has good chemical resistance. It is a high solids product. This product contains no solvents on the Hazardous Air Pollutants (HAPs) list. Minor amounts of such solvents may come in through tinting of some colors. To be used as topcoat in atmospheric environments.

### Typical use

Protective:

Recommended for bridges and buildings. Suitable for a wide range of industrial structures.

Marine:

Recommended for topside, deck and superstructure.

### Approvals and certificates

This product contributes to the Green Buildings Standard credits. Please see section Green Building Standards.

Additional certificates and approvals may be available on request.

### Colors

according to Multicolor Industry tinting system (MCI)

### Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	73 ± 2 %
Gloss level (GU 60 °)	ISO 2813	gloss (70-85)
Flash point	ISO 3679 Method 1	90 °F (32 °C)
Density	calculated	1.5 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested) (CARB(SCM)2007, SCAQMD rule 1113, Hong Kong)	2.03 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.

All data is valid for mixed paint.

Gloss description: According to Jotun Performance Coatings' definition.

The VOC values refer to white colour.

## Film thickness per coat

### Typical recommended specification range

Dry film thickness	2.4 mils (60 µm)	- 4 mils (100 µm)
Wet film thickness	3 mils (80 µm)	- 6 mils (140 µm)
Theoretical spreading rate	490 ft <sup>2</sup> /gal (12 m <sup>2</sup> /l)	- 300 ft <sup>2</sup> /gal (7.3 m <sup>2</sup> /l)

## Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

## Application

### Application methods

The product can be applied by

Spray:	Use air spray or airless spray.
Brush:	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller:	May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Hardtop Eco Comp A	4 part(s)
Hardtop Eco Comp B	1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 26 / Jotun Thinner No. 10

Jotun Thinner No. 26 shall be used, if HAPs free is a criteria.  
No thinner shall be used in LEED projects in order to honor the LEED v4 regulation.  
Jotun Thinner No. 10 can be used where aromatic solvents are accepted.

Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.

### Guiding data for airless spray

Nozzle tip (inch/1000): 13-19  
Pressure at nozzle (minimum): 150 bar/2100 psi

### Guiding data for air spray

Nozzle tip: HVLP: 11-19 (inch/1000) / Pressure pot: 1.1-1.9 (mm)  
Pressure at nozzle (minimum): HVLP: 2.1 bar/30 psi / Pressure pot: 2.1 bar/30 psi

## Drying and Curing time

Temperatures:  
-10°C = 14°F / -5°C = 23°F / 0°C = 32°F / 5°C = 41°F / 10°C = 50°F / 15°C = 59°F / 23°C = 73°F / 35°C = 95°F / 40°C = 104°F / 100°C = 212°F

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	4 h	2 h	1 h
Walk-on-dry	16 h	8 h	4 h
Dried to over coat, minimum	10 h	5 h	3 h
Dried/cured for service	10 d	5 d	3 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Temperatures: 15°C = 59°F / 23°C = 73°F

<b>Paint temperature</b>	<b>23 °C</b>
Pot life	2 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C

Resistant to spills of most oils, aliphatic petroleum products and non aggressive chemicals.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, zinc epoxy, epoxy mastic, polyurethane  
Subsequent coat: polyurethane

## Packaging (typical)

	Volume (liters)	Size of containers (liters)
Hardtop Eco Comp A	16	20
Hardtop Eco Comp B	4	5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

### Shelf life at 73°F (23 °C)

Hardtop Eco Comp A	48 month(s)
Hardtop Eco Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Green Building Standards

This product contributes to Green Building Standard credits by meeting the following specific requirements:

#### LEED®v4 (2013)

EQ credit: Low emitting materials

- VOC content for Industrial Maintenance Coatings (250 g/l) (CARB (SCM) 2007) and emissions lower than or equal to 0.5 mg/m<sup>3</sup> (CDPH method 1.1).

MR credit: Building product disclosure and optimization

- Material Ingredients, Option 2: Material Ingredient Optimization, International Alternative Compliance Path - REACH optimization: Fully inventoried chemical ingredients to 100 ppm and not containing substances on the REACH Authorization list – Annex XIV, the Restriction list – Annex XVII and the SVHC candidate list.

- Environmental Product Declarations. Product-specific Type III EPD (ISO 14025;21930, EN 15804).

#### LEED® (2009)

- IEQ Credit 4.2: The VOC requirements of Green Seal Standard GC-03, 1997.

#### BREEAM® International (2016)

- Mat 01: Product-specific Type III EPD (ISO 14025;21930, EN 15804).

#### BREEAM® NOR (2012/2016)

- Mat 1.5/01: This product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

#### BREEAM® NOR (2012)

- Hea 9: VOC content for Two-pack performance Coatings SB (500 g/l) (EU Directive 2004/42/CE) and emission demands (ISO 16000-series).

This product is tested by RISE Research Institutes of Sweden/SP Technical Research Institute of Sweden or Eurofins in accordance with ISO 16000-series and CDPH method 1.1 (2010)/1.2 (2017), and passes the demands of the French AFSSET (2011), German AgBB (2017) and Belgian decree (2014).

The EPDs are available at [www.epd-norge.no](http://www.epd-norge.no)

## Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

---

## Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---