

JOTUN Sparkel vegg og tak medium (tube)

Product description

Type

Light filler to be used indoors in dry rooms.

Features and benefits

Can be levelled in thickness 0-4 mm without cracking. Minimal shrinkage. Very good adhesion to the surface.

Recommended use

Joint and spot treatment on gypsum boards and other boards.
Can also be used for smoothing out plaster and concrete.



23°C - 50% R.H. 23°C - 50% R.H.



Product data

Generic type	Based on cellulose derivatives added lightweight fillers combined with crushed dolomite marble.
Solids by volume	52 ± 2 volume%
Specific gravity	1
Particle size	0 - 0.2 mm

Application data

Spreading rate per coat (m²/liter)

Spreading rate per coat: 0- 1 m²/liter.

Drying times

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Dust dry	30 min.
Surface (touch) dry	24 h
Recoatable, minimum	24 h

Example of how drying times for air drying filler change at different relative humidity and temperature

Drying times in hours.

Temperature

Relative Humidity (RH)

	10 %	20 %	30 %	40 %	50 %	60 %	70 %	80 %	85 %	90 %	95 %
10 °C	21	23	26	29	36	42	54	72	96	144	288
15 °C	14	16	18	20	24	29	38	54	72	108	192
20 °C	10	11	12	14	17	20	26	38	48	72	144
25 °C	7	8	9	10	12	14	19	27	34	39	96

This table shows an example of change in drying times for the second time jointing of gypsum board joints. The table also has relevance for **JOTUN Sparkel vegg og tak medium** in relation to drying times in adverse climatic conditions.

Avoid using filler when the drying times conditions are the same as for the numbers in red. Deviations from this can have negative consequences for the filler work done!

Directions for use

Substrate	

Disposal of waste



Environmental labelling




2097 0010

The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Approvals

CE-marking



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: Not to be declared



Miscellaneous

Contact information

Jotun Danmark A/S
Jernet 6
6000 Kolding

Tel: +45 76 30 32 00
mail@jotun.dk

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.

