

Megaprimer Lite

Product description

This is a two component polyamide cured epoxy coating. Designed as a fast drying, sandable finishing primer. Can be used as primer as a part of a complete system in atmospheric and immersed environments.

Typical use

Exterior and interior areas, including hulls, above and below waterline, superstructures and decks. To be used as finish primer under Megagloss range of products. Suitable for properly prepared carbon steel, stainless steel, aluminum, composite and coated surfaces as epoxy systems and polyurethane systems. Can be used as primer or sealer for fillers in atmospheric and immersed environments.

Colors

grey, white

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	51 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
Flash point	ISO 3679 Method 1	77 °F (25 °C)
Density	calculated	1.2 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	3.8 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.

Gloss description: According to Jotun Performance Coatings' definition.

The above data is valid for mixed, non-diluted product.

Film thickness per coat

Typical recommended specification range

Dry film thickness	2 mils (50 µm)	3 mils (75 µm)
Wet film thickness	4 mils (100 µm)	6 mils (150 µm)
Theoretical spreading rate	420 ft ² /gal (10.2 m ² /l)	280 ft ² /gal (6.8 m ² /l)

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 3 (ISO 8501-1) or SSPC SP-3	Sa 2½ (ISO 8501-1) or NACE No. 2 / SSPC SP-10
Stainless steel	The surface shall be machine abraded with non-metallic abrasives or bonded fibre machine to impart a scratch pattern of min. 45 µm to the surface and to remove all polish from the surface.	Abrasive blast cleaning to achieve a surface profile using non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Aluminum	The surface shall be hand or machine abraded with non-metallic abrasives or bonded fibre machine or hand abrasive pads to impart a scratch pattern to the surface.	Abrasive blast cleaning to achieve a surface profile using non-metallic abrasive media which is suitable to achieve a sharp and angular surface profile.
Shop primed steel	Sa 2 (ISO 8501-1) / SP 6 / NACE No. 3 (SSPC-VIS 1)	Sa 2 (ISO 8501-1) / SP 6 / NACE No. 3 (SSPC-VIS 1)
Galvanized steel	The surface shall be clean, dry and appear with a rough and dull profile.	The surface shall be clean, dry and appear with a rough and dull profile.
Coated surfaces	<p>New Jotun Yachting epoxy primer: Clean, dry and undamaged compatible coating. Remove any contamination that could interfere with the intercoat adhesion.</p> <p>Cured Jotun Yachting epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminum oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats, depending on condition.</p> <p>Fillers: Orbital sanding or hand sanding with aluminum oxide or silicon carbide sand paper with grit P100-P160.</p>	<p>New Jotun Yachting epoxy primer: Clean, dry and undamaged compatible coating. Remove any contamination that could interfere with the intercoat adhesion.</p> <p>Cured Jotun Yachting epoxy primer or polyurethane topcoat: Exceeding maximum recoat intervals will require cleaning/abrading by orbital sanding or hand sanding with aluminum oxide or silicon carbide sand paper with grit P120-P160, and/or application of additional coats, depending on condition.</p> <p>Fillers: Orbital sanding or hand sanding with aluminum oxide or silicon carbide sand paper with grit P100-P160.</p>

Composite	Epoxy Composites should be free from any wax or mould release coating before starting any surface perpetration. Random orbital sanding of the surfaces thoroughly to achieve an even profile by abrading the surface using P80-P120 grit aluminum oxide paper or silicon carbide sand papers. NOTE: For the coating of Unsaturated Polyester based composites, please contact your local Jotun office.	Epoxy Composites should be free from any wax or mould release coating before starting any surface perpetration. Random orbital sanding of the surfaces thoroughly to achieve an even profile by abrading the surface using P80-P120 grit aluminum oxide paper or silicon carbide sand papers. NOTE: For the coating of Unsaturated Polyester based composites, please contact your local Jotun office.
Galvanized steel	The surface shall be clean, dry and appear with a rough and dull profile.	The surface shall be clean, dry and appear with a rough and dull profile.

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

Jotun recommends no more than 2 steps of sandpaper grades when moving between grades.

Application

Application methods

The product can be applied by

- Spray: Use air spray or airless spray. Care must be taken to achieve the specified dry film thickness.
- Brush: Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
- Roller: May be used for small areas. Not recommended for first primer coat. Care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

Megaprimer Lite Comp A	4 part(s)
Megaprimer Comp B	1 part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

Guiding data for airless spray

Nozzle tip (inch/1000):	15-21
Pressure at nozzle (minimum):	150 bar / 2100 psi

Guiding data for air spray

Nozzle tip:	Pressure pot: 1.2-1.4 (mm)
Pressure at nozzle (minimum):	Pressure pot: 2.5-3 bar

Drying and Curing time

Temperatures:

-10°C = 14°F / -5°C = 23°F / 0°C = 32°F / 5°C = 41°F / 10°C = 50°F / 15°C = 59°F / 23°C = 73°F / 35°C = 95°F / 40°C = 104°F / 100°C = 212°F

Substrate temperature	10 °C	23 °C	40 °C
Comp A + Comp B			
Surface (touch) dry	2 h	1 h	30 min
Walk-on-dry	14 h	6.5 h	3 h
Dried to over coat, minimum	24 h	12 h	9 h
Dried/cured for service	14 d	7d	3 d
Comp A + Comp B + Thinner			
Surface (touch) dry	2.5 h	1.5 h	45 min
Walk-on-dry	20 h	9 h	4 h
Dried to over coat, minimum	30 h	16 h	12 h
Dried/cured for service	14 d	7 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Drying time will increase with increasing film thickness.

When product is diluted to help spraying with conventional spray equipment, it is required to allow to dry for 48 hours and dry sand the surface with P220/P320.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Temperatures: 15°C = 59°F / 23°C = 73°F

Paint temperature	23 °C
Induction time	30 min
Pot life	8 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, polyurethane

Subsequent coat: epoxy, polyurethane

Packaging (typical)

	Volume (liters)	Size of containers (liters)
Megaprimer Lite Comp A	0.8 / 4 / 16	1 / 5 / 20
Megaprimer Comp B	0.2 / 1 / 4	0.375 / 1 / 5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C)

Megaprimer Lite Comp A	24 month(s)
Megaprimer Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.