

## Fenomastic Güzel Evim Saf İpek

### Product description

#### Type

This product is a superior quality emulsion paint, designed for interior surfaces with a good colour experience due to its colour accuracy. Based on PVA emulsion.

#### Features and benefits

Offers a wide range of long lasting colours. It has enhanced washability with good hiding power and flow, giving walls a smooth silky finish. Offers incan anti bacterial properties. Has very low VOC which ensures good indoor air quality. Free from harmful chemicals like APEO, formaldehyde, heavy Metals etc.

#### Recommended use

Specially formulated topcoat recommended for all indoor spaces, including residential areas, villas and hotels.

#### Substrate

Cement plaster, concrete, block work, rendered surfaces, gypsum board etc.

### Product data

<b>Packaging size</b>	1 L, 2 . 5 L and 15 L		
<b>Colours</b>	As per colour card and available in Jotun Multicolor tinting system (Interior range).		
<b>Solids</b>	38 ± 2 volume%	Theoretical	
<b>Specific gravity</b>	1,36		
<b>VOC</b>	1	g/l	ISO 11890 EU

### Application data

#### The product can be applied by

Roller : Recommended.

Brush : Recommended to paint corners and edges.

Spray : Use airless spray or conventional spray.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.46-0.53 mm (0.018-0.021")
<b>Spray angle degrees</b>	65°- 80°
<b>Pressure at nozzle</b>	15 MPa (100 kp/cm <sup>2</sup> , 1400 psi)

#### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Recommended film thickness per coat

<b>Dry</b>	Minimum	25 µm
<b>Dry</b>	Maximum	35 µm
<b>Dry</b>	Typical	30 µm
<b>Wet</b>	Minimum	66 µm
<b>Wet</b>	Maximum	92 µm
<b>Wet</b>	Typical	79 µm

Film thickness will vary and are calculated as an average.

### Spreading rate per coat

<b>Theoretical</b>	Minimum	10,8 m <sup>2</sup> /l
<b>Theoretical</b>	Maximum	15,2 m <sup>2</sup> /l
<b>Theoretical</b>	Typical	12,6 m <sup>2</sup> /l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

### Thinner

Water

### Dilution

Maximum 10 %

### Cleaning of painting tools

Water

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface must be sanded to achieve maximum adhesion if the application is done after recommended recoating time.

#### Relative Humidity (RH) 50 %

<b>Substrate temperature</b>	10 °C	23 °C	40 °C
<b>Surface (touch) dry</b>	2 h	1 h	0.5 h
<b>Hard dry</b>	48 h	24 h	12 h
<b>Dry to over coat, minimum</b>	6 h	3 h	1.5 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

#### Primer

Fenomastic Emulsion Primer or PVA Primer : 1 Coat

### Filler

Stucco : 2 Coats

### Topcoat

Fenomastic Güzel Evim Saf İpek : 2 Coats

### Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.