

Fenomastic Güzel Evim Zengin Mat

Product description

Type

This product is a superior quality emulsion paint, with enriched colour experience due to the accuracy of colours and its matt finish. Based on 100% pure acrylic emulsion.

Features and benefits

Offers a wider selection of colours which come out more beautifully because of the matt finish. Deep colours look rich, strong colours look soft as they are undisturbed by gloss. It also has enhanced film properties and provides washable matt finish. Has very low VOC which ensures good indoor air quality. Free from harmful chemicals like APEO, formaldehyde, heavy Metals etc. Offers good flow, hiding power, incan anti bacterial and colour retention properties.

Recommended use

Specially formulated topcoat recommended for all indoor spaces, including residential areas, villas and hotels.

Substrate

Cement plaster, concrete, block work, rendered surfaces, gypsum board etc.

Product data

Packaging size	1 L, 2.5 L and 15 L		
Colours	Refer to Fenomastic colour card.		
Solids	34 ± 2 volume%	Theoretical	
Specific gravity	1,31	Only for white colour	
VOC	8	g/l	ISO 11890 EU
VOC-USA	6,97	g/l	EPA Method 24

Application data

The product can be applied by

Roller : Recommended.

Spray : Use airless spray or conventional spray.

Brush : Recommended to paint corners and edges.

Guiding data for airless spray

Nozzle tip	0.021" - 0.027"		
Spray angle degrees	65°- 80°		
Pressure at nozzle	140 - 190 kg/cm ² (2100 psi)		

Conditions during application

Technical Data Sheet

Fenomastic Güzel Evim Zengin Mat



The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Recommended film thickness per coat

Dry	Minimum	25 µm
Dry	Maximum	35 µm
Dry	Typical	30 µm
Wet	Minimum	73 µm
Wet	Maximum	102 µm
Wet	Typical	88 µm

Film thickness will vary and is calculated as average.

Spreading rate per coat

Theoretical	Minimum	11,3 m ² /l
Theoretical	Maximum	13,6 m ² /l
Theoretical	Typical	10 m ² /l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

Thinner

Water

Dilution

Maximum 10 %

Cleaning of painting tools

Water

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface must be sanded to achieve maximum adhesion if the application is done after recommended recoating time.

Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	12 h	6 h	2 h
Hard dry	16 h	8 h	4 h
Dry to over coat, minimum	12 h	6 h	2 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Technical Data Sheet

Fenomastic Güzel Evim Zengin Mat



Recommended paint system

Primer

Fenomastic Emulsion Primer or PVA Primer : 1 Coat

Filler

Stucco : 2 Coats

Topcoat

Fenomastic Güzel Evim Zengin Mat : 2 Coats

Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Certificates

Surface spread of flame : Class 1Y (In accordance with the class definitions given in BS 476:Part 7:1997) : **Exova Warringtonfire, UK.**

Wet Abrasion scrub test as per DIN 53778 passed for 5000 cycles as tested by Al Futtaim Bodycote Testing LLC, UAE

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

Technical Data Sheet

Fenomastic Güzel Evim Zengin Mat

