

JOTUN Linoljemaling

Product description

Type

Traditional linseed oil-zinc white paint for exterior and interior use. Film preserving agent against surface fungus added. **JOTUN Linoljemaling** is developed according to advice from Riksantikvaren.



Features and benefits

Real linseed oil based paint has a yellow colour and can result in deviation on some colours. Linseed oil is a vegetable oil and will wear down when exposed to sunlight, weather and wind. This natural chalking will affect the colour in time. Linseed oil based paint works as an offering layer for the wood and is ment to wear down in time. Colour/gloss will reduce when the paint gets older. The chalking is a natural property for the linseed oil in protection of the wood.

Product data

Tinting	Bases must be tinted using Jotun Multicolor . Bases must not be used unless tinted.
Gloss level	Semi gloss
Solids by volume	75 ± 2 volume%
Specific gravity	1.5 white
Flash point	68 °C
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/d): 300 g/l. The product contains max 206 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed.
Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Perform a test application.

Application equipment / methods

Brush.
It is particularly important to apply linseed oil based paint in thin layers to ensure good dry through and to prevent crawling/sun blisters.
The product is not to be used for spray application.

Cleaning of painting tools

JOTUN Penselrens and water or a suitable cleaning agent and water.

Thinner

JOTUN White Spirit

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended, sawn wood:	6 - 9	111 - 167	83 - 125
Recommended, planed wood:	10 - 20	50 - 100	38 - 75
Comments:	Dependent on the surface texture.		

Drying times

Non sticking after 24 hours.

Paintable after 48-60 hours. The drying time depends on the temperature (min. +10 °C), absorption, humidity and air circulation.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Air temperature	23 °C
Substrate temperature	23 °C

Surface (touch) dry	24 h
Recoatable, minimum	48 h - 72 t

Directions for use

The substrate must be clean, sound and dry.

Substrate	Treatment
Untreated wood:	<p>Contaminated, untreated substrates to be washed with JOTUN 3-i-1 Kraftvask og Træ- og Murrens. Untreated wood must be primed with JOTUN Linoljemaling with 20 % JOTUN White Spirit. On less absorbent surfaces, add only 10 % JOTUN White Spirit. Saturate all end grains/cut surfaces thoroughly, apply 3-4 coats wet-on-wet.</p> <p>Thinned JOTUN Linoljemaling is fresh produce. Thinned linseed oil based paint should not be stored for use the next day. The paint must be stirred before and during painting.</p> <p>Recommended end treatment: JOTUN Linoljemaling. Apply 2 thin layers to planed wood and 1-2 thin layers to unplanned wood. Thin the first coat 10 % with JOTUN White Spirit. Always apply the last coat undiluted.</p>
Previously treated wood:	<p>Painted surfaces must be washed with JOTUN 3-i-1 Kraftvask og Træ- og Murrens and matted mechanically. Remove weathered wood and loose paint by Speed Heater IR and or wire brushing/scraping. If clean wood is infested with black fungus, apply JOTUN Sopp- og algefjerner. The treatment should dry on the wall. Saturate bare wood with primer - JOTUN Linoljemaling added 10 % JOTUN White Spirit.</p> <p>Thinned paint is a fresh product and should not be kept until the next day. The paint must be stirred before and during painting.</p> <p>Recommended end treatment: JOTUN Linoljemaling. Apply 2 thin layers to planed wood and 1-2 thin layers to unplanned wood.</p>

Always apply the last coat undiluted.

Additional information

Due to danger of ignition, used cloths must be burned immediately or soaked in water. See Jotun's swatches for Linseed oil based paint and the Directorate for Cultural Heritage's Informasjonsblad om Linoljemaling - nr 3.9.4 (www.ra.no)

Maintenance

Annual house wash with **JOTUN 3-i-1 Kraftvask og Træ- og Murrens** (mixing ratio with water 1:15) is recommended for fouling. Exposed walls should also be treated with **JOTUN Sopp- og algefjerner** after washing.

Storage

The quality of a tinted product will reduce when stored more than one year. In storage and in transport keep the container upright.

Disposal of waste

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: 4471783

Safety rules

1-1

1993

Miscellaneous

Contact information

Jotun Danmark A/S
Jernet 6
6000 Kolding

Tel: +45 76 30 32 00
mail@jotun.dk

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.