

LADY Minerals Sealer

Product description

Type

LADY Minerals Sealer is a transparent treatment that provides durability and water resistance.



Recommended use

For indoor use in dry rooms, for smaller surfaces that are exposed to wear.

23°C-50% R.H.



Vann/JOTUN Penselrens

Product data

Packaging size	0.75 L
Gloss level	03
Generic type	Acrylic emulsion
Solids by volume	30 ± 2 volume%
Specific gravity	1050
pH value	8 to 9
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/f): 130 g/l. The product contains max 2 g/l VOC.

Application data

Remarks

Stir well before use. Contents of tins with different production numbers should be mixed.

Application equipment / methods

18 cm Jordan Ultimate roller for smooth substrates.
When using tape, Tesa Sensitive for sensitive surfaces or similar is recommended.

Cleaning of painting tools

Water and **JOTUN Penselrens**.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)

Recommended: 8 – 10 100 – 125 30 – 38

Thinner

The product is ready to use and should not be thinned.

Conditions during application

Air and surface temperature must be above +10 °C during application.

Drying times

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Surface (touch) dry	1 h
Fully cured	4 weeks

Directions for use

Surface preparation

When treating with **LADY Minerals Sealer**, the best result is obtained if two coats of **LADY Minerals** lime paint are applied first, before the sealer. The curing time for **LADY Minerals** lime paint is 24 hours. **LADY Minerals Sealer** is applied after one day, so that the lime paint gets hardened properly.

Topcoat

1 x **LADY Minerals Sealer** to be applied evenly and in full lengths with a roller on top of **LADY Minerals**. Recommended roller: 18 cm Jordan Ultimate roller for smooth substrates. Roll whole lengths without overlapping and post-roll. Make sure that **Sealer** does not leave any excess after the ends of the roller. The sealer should penetrate into the substrate, but not form excess (whitish film). **LADY Minerals Seal** can give a deeper colour appearance. Perform a test application. We recommend applying only one coat on top of **LADY Minerals** lime paint.

Additional information

In storage and in transport keep the container frost free and upright.

Maintenance

The use of micro fiber cloth with water is recommended.

Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Disposal of waste

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

50445515

NOBB module number

42025375

Contact information

Jotun A/S
Box 2021
NO-3202 Sandefjord
Norway

Tel.: +47 33 45 70 00

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.