

Jotatherm CSP1 Scrim

Product description

An e-glass fibre and polyester scrim. Specially woven fabric to be installed within Jotatherm TB550 coating when used as a cryogenic spill protection system.

Typical use

Cryogenic spill resistance:

Used only as a system component when installing Jotatherm TB550 to protect steel substrates from embrittlement due to cryogenic release such as LNG spills.

For cryogenic spill resistance applications Jotatherm CSP1 Scrim must be installed as detailed in the Jotatherm TB550 Application Guide (AG).

Colors

White with identifying red stitch

Product data

The scrim is identified with a red stitching thread every 3.93 inches (100 mm).

The stitching gauge is 1 thread per 1/3rd inch (8.5 mm).

The e-glass fibre has a linear density of 300tex.

Weight of 3.95 oz. per 10.7 Square Feet (112 grams per m²).

Packaging (typical)

Roll weight is 13.86 lbs (14 kg).

Roll length is min. 328 feet (100 meters).

Roll width is 4.16 feet (1.27 meters).

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., and application quality. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
