

JOTAPROFF Fasadeakryl

Product description

Type

A well pigmented acrylic paint. To be used in combination with **VISIR Oljegrunning**, as part of a system treatment.



Features and benefits

Contains effective film conserving agent that counteract mould growth. The high pigment content protects the wood against sunlight disruptive effect and gives a very good weatherability.

Recommended use

For exterior use on facades and woodwork.



Product data

Packaging size	According to the current price list.
Base availability	White, A, B, C and oxide red. Bases must not be used unless tinted.
Generic type	Based on acrylate.
Solids by volume	35 ± 2 volume%
Specific gravity	1.3 White
pH value	8.2 to 8.9
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 80 g/l VOC.

Application data

Remarks

To ensure long durability it is important to apply a sufficient amount on edges and planed surfaces, min. 3 coats (100 µm dry paint film). Sand down sharp edges. Remember to coat end grain.

Can not be mixed with other paint products and do not mix in oil additives.

The product is water borne.

The product shall not be thinned.

Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Linseed oil / oils in the substrate can cause blisters and flaking. Sun on semi-dry paint may cause skin drying and sun blisters. Painting on fire protected cladding may cause salt precipitation/flaking.

Bases must be tinted using **Jotun Multicolor**. Content of cans from different productions and different tinting systems may cause shade differences. Measures one can take to avoid colour differences:

- Mix the content in cans with different batch numbers together. Stir well. The production number can be found after the letters SZ or SV on the label in the front of the can.
- It is advantageous to use the same batch number within the same defined area. Changing the can in the middle of the wall or confined area, increases the possibility of a visible colour difference.
- There may be colour differences of paint which are mixed on different tinting machines and / or at different times. Please be aware of this if you need to buy more paint / opaque stain / stain for the same project at a later time.
- If you notice any visible differences, contact your point of sale or Jotun Technical Service (tel. +47 33457530).

Application equipment / methods

Brush, roller or spray.

Guiding data for airless spray

Nozzle tip	0.46 mm (0.018")
Spray angle degrees	65–80°
Pressure at nozzle	15–18 MPa (150–180 kg/cm ²)

Cleaning of painting tools

Water and **JOTUN Penselrens** or water and a suitable cleaning agent.

Dilution

Do not mix in oil additives.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended, sawn wood:	7 – 10	100 – 143	35 – 50
Recommended, planed wood:	10 – 12	83 – 100	29 – 35

Conditions during application

Air and surface temperature must be above +5 °C during application.

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

- High humidity (RH%) significantly prolongs the drying time for waterborne products.
- Warm air can hold more moisture than cold air, and in case of temperature drop this can cause condensation.
- Stagnant air retards the drying, and can provide higher risk of condensation.
- Low temperature and condensation can provide inadequate film formation/curing.

When there is a risk of condensation, finish the painting in time to dry before condensation occur.

The product contains effective agents against surface mould. In unfavorable drying and curing conditions, a visible yellow discoloration on the surface might occur. This is a surface phenomenon that will disappear after some time under the influence of light and UV rays. The phenomenon will not affect the product's effectiveness against surface fungi or otherwise impair the product's quality and durability.

Drying times

Variations by changes in temperature, humidity, wind conditions and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Air temperature	23 °C	15 °C	5 °C
Substrate temperature	23 °C	15 °C	5 °C

Dust dry	0.5 h	1 h	1.5 h
Recoatable, minimum	2 t	3 t	6 t

TØRKETID/ TØRRETID/ TORKTID/ DRYING TIME	Støvtørr/Dammtørr/Dust dry	0t(h)	0,5t(h)	1t(h)	1,5t(h)	Ved ca. 50 % luftfuktighet/ At approx. 50 % moisture
		+23°C	+15°C	+5°C		
Overmalbar/Övermålningsbar/Dry to recoat		0t(h)	2t(h)	3t(h)	6t(h)	
		+23°C	+15°C	+5°C		

Directions for use

The substrate must be clean, sound and dry.
 For the best possible edge coverage, sand down sharp edges.

Substrate	Treatment
New woodwork:	Before or immediately after installation of new woodwork, treat with a brush coat of VISIR Oljegrunning . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 3 coats JOTAPROFF Træbeskyttelse on new planed woodwork and 2 coats on on new sawn woodwork.
Fresh wood left untreated for more than 4 weeks:	Should be cleaned using JOTUN 3-i-1 Kraftvask og Træ- og Murrens and brushed with a wire brush. Apply VISIR Oljegrunning to bare woodwork. The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 3 coats JOTAPROFF Træbeskyttelse on new planed woodwork and 2 coats on on new sawn woodwork.
Previously treated wood:	Should be cleaned using JOTUN 3-i-1 Kraftvask og Træ- og Murrens . Remove loose paint/stain and wood fibers by wire brush or scraping. Sand glossy and hard surfaces. Bare spots (from drybrushing/scraping) to be primed with VISIR Oljegrunning . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 2 coats JOTAPROFF Træbeskyttelse .
Gutters, fascias made of plastic and metal commonly used on buildings:	Should be cleaned using JOTUN 3-i-1 Kraftvask og Træ- og Murrens . Bare metal to be primed with two coats suitable primer. Apply 2 coats JOTAPROFF Træbeskyttelse .

Maintenance

Wash the house with **JOTUN 3-i-1 Kraftvask og Træ- og Murrens** when necessary.

Management, Operation and Maintenance

Please refer to the Drift og Vedligeholdelse datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste



Empty and dry pails can be sorted together with plastic packaging. The metal handle must be removed and be sorted with metallic packaging. See the QR code for more information.



Sorted as plastic



Remove the handle

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

Environmental labelling



2097 0003

The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Green Building Standards

The declared product contributes to Green Building Standard credits by meeting the following specific requirements:

- Swan (2097 0003)
- Property criteria in BASTA (2018:A2)
- Class B according to Bedømningskriterier (Assessment Criteria) 6.0 for SundaHus (2013)

BREEAM® International (2016)

Mat 01: Product-specific Type III EPD (ISO 14025, ISO 21930, EN 15804) for Scandinavia.

Mat 01: The product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

BREEAM® NOR (2012)

Mat 1.3: Product specific type III EPD (ISO 14025, ISO 21930, EN 15804) for Scandinavia.

Mat 1.5: This product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

Additional certificates and approvals may be available on request.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: 2480109

Safety rules

00-1

1993

Contact information

Jotun Danmark A/S
Jernet 6
6000 Kolding
Tlf.: +45 76 30 32 00
Mailadresse: mail@jotun.dk

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.