

## BUTINOX Interiør Tavlemaling

### Product description

#### Type

A water based, specially developed matt acrylic paint for making blackboards.

#### Features and benefits

Solvent free and low odor blackboard paint that can be applied in many colors and which is easy to write on with chalk.

#### Recommended use

Used indoors as intermediate and topcoat on smooth walls and surfaces such as boards, plaster and filler in dry areas. To make the best possible blackboard, the substrate should be as even and smooth as possible.

### Product data

<b>Packaging size</b>	According to the current price list.
<b>Base availability</b>	C
<b>Tinting</b>	Bases must be tinted using <b>Butinox Colour Manager</b> .
<b>Gloss level</b>	2
<b>Solids by volume</b>	40 ± 2 volume%
<b>Specific gravity</b>	1.2
<b>pH value</b>	8.5
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/a): 30 g/l. The product contains max 1 g/l VOC.

### Application data

#### Remarks

Contents of tins with different production numbers should be mixed. Stir well.

#### Application equipment / methods

The paint shall be applied rich and evenly with a roller. Roller for smooth surfaces is recommended. You can also use a brush.

#### Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended:</b>	8 - 10	100 - 125	40 - 50

### Cleaning of painting tools

Clean with water and soap.

### Thinner

Shall not be thinned.

### Conditions during application

Temperature of substrate and air must be minimum +10 °C.

### Drying times

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Dust dry	1 h
Recoatible, minimum	2 h
Dry to use / careful use	7 days

The coating must cure for at least 7 days before using chalk on the blackboard.

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry. Surfaces to be washed with **BUTINOX Interiørvask**, matted and dedusted.

### Topcoat

**BUTINOX Interiør Tavlemaling**. Apply two coats.

### Additional information

See [www.butinoxinteriør.no](http://www.butinoxinteriør.no) for more information.

### Cleaning of spillage

**BUTINOX Interiørvask**

### Maintenance

Clean blackboard chalk with water and cloth. If the board is very dirty, you can use light soapy water and cloth. The pH of the soapy water must not exceed 8.5.

### Storage

In storage and in transport keep the container frost free and upright.

### Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

## Approvals



**Recommended by the Swedish Astma- och Allergiförbundet.** Asthma- och allergiförbundets recommendation does not apply during application of the paint. It does not apply until 14 days after application (TVOC <10 mcg / m<sup>3</sup> / h). Exercise caution and ventilate during curing time (2 weeks).

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

Product registration number: Not to be declared

Safety rules	
00-1	1993

---

## Miscellaneous

### Contact information

Jotun Danmark A/S  
Jernet 6  
6000 Kolding

Tel: +45 76 30 32 00  
mail@jotun.dk

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.