

JOTAPROFF AquaTech

Product description

Type

Silky matt paint for bathrooms and wet rooms.

Features and benefits

Included in Jotun's approved wet room system.

Recommended use

Can be used as a waterproof and water-repellent finish on walls / ceilings in damp / wet areas in hospitals, food processing facilities and other places where a durable and moisture-resistant surface is required. The paint contains anti fungal agents. The product is recommended for indoor use only. The product is part of Jotuns Våtromssystem (Jotun's wet room system) recommended by Fagrådet for Våtrom (Norwegian wet room council).

See jotun.no, and further down in this data sheet, for detailed description of the system structure.

Substrate

Approved substrates in the system are concrete, plaster and plasterboard (gypsum board). Chipboard for wetroom is not an approved surface for Jotuns Våtromssystem.



Product data

Packaging size	3 L (filling level 2.7 L) and 10 L (filling level 9 L)
Base availability	White, A, B and C
Tinting	Bases must be tinted using Jotun Multicolor . Up to 10 % with Jotun Multicolor colorants.
Colours	White base may be used untinted as White.
Gloss level	Silky matt 10

Glansgradtabell for JOTAPROFF AquaTech 10



Generic type	Acrylic paint
Solids by volume	41 ± 2 volume%
Specific gravity	1.4
pH value	8.3 to 9.6
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/a): 30 g/l. The product contains max 1 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed. Stir well before use.
Follow the installation instructions (jotun.no) when using Jotuns Våtromssystem (Jotun's wet room system).

Application equipment / methods

Roller, brush or airless spray.

Guiding data for airless spray

Nozzle tip	0.53 mm (0.021")
Spray angle degrees	65–80°
Pressure at nozzle	15 MPa (150 kg/cm ²)

Cleaning of painting tools

Water and **JOTUN Penselrens** or water and a suitable cleaning agent.

Thinner

Shall not be thinned.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	8 – 10	100 – 125	41 – 51

Conditions during application

Air and surface temperature must be above +10 °C during application.

Cleaning of spillage

JOTUN Spezial wipen are recommended to clean spillage. **JOTUN Spezial wipen** are a convenient washing/cleansing wipe for use before and during paint work.

Drying times

Drying times deviate because of changes in temperature, air humidity, air circulation and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Surface (touch) dry	1 h
Recoatable, minimum	4 h
Dry to use	10 days
Fully cured	10 days

At least 10 days before the area is exposed to water.

Directions for use

Waterproof system structure

Surface preparation: The substrate must be clean, sound and dry. Clean with **JOTUN Spesialvask før maling**. Unevenness in the substrate, screw holes, plate joints, and in and out corners are filled with **JOTUN Våtromssparkel**. On slabs, the outgoing corners must be reinforced with a corner bracket and the joints will be reinforced with a paper strip.

Transition between wall and floor: When using vinyl coatings on the floor, woven fabric must overlap at least 25 mm of the floor coverings' socket. **JOTUN Gunning og lim for våtrom** and **JOTAPROFF AquaTech** are applied at least 3 mm below the woven fabric to seal the edge thereof. Fill the gap between the socket and the wall with **JOTUN Sparkel våtrom**. Floor coatings made of PVC with PUR surface are well sanded, stripped and degreased to get the best adhesion in overlap between floor coverings and painted wet room systems.

When installing tiles as a socket, the wall must be finished with the entire paint system before installing the socket. The paint system must overlap the floor membrane by at least 25 mm. After tiling the socket, seal the edge between the tiles and the paint system with Casco AquaSeal.

Pipe feeds: Cut a V-joint around the pipe feeds, which is primed using **JOTUN Gunning og lim for våtrom** diluted with water in the ratio 2:1. Drying time is at least 4 hours. Then fill the joint with Casco AquaSeal. In addition, wall cushions can be covered with a cuff for pipe-in-pipe systems. Cuffs are glued firmly to the surface with Casco AquaSeal.

Primer: All absorbent substrates to be primed with **JOTUN Gunning og lim for våtrom** diluted with water in the ratio 2:1. Consumption approx. 15 m² / liter. Drying time is at least 4 hours.

Wall coverings: Apply **JOTUN Gunning og lim for våtrom**, undiluted. Consumption 4-5 m² / liter. Use a long-haired roller. Hang **JOTUN Glassfiberstrie Fin Våtrom** / **JOTUN Glassfiberstrie Lav Våtrom**. Make sure that **JOTUN Gunning og lim for våtrom** does not become surface dry before installing the woven fiberglass fabric. Hang the wallcovering lengths edge-to-edge on the surfaces and with 1 cm overlap in inbound corners. Hang maximum 2 lengths at a time. It is important to remove all blisters that may occur. This is best done with a stiff plastic trowel that is rounded at the edges with abrasive paper. Make sure that all wall coverings are pressed firmly against the adhesive. If the wall covering is lifted from the substrate during installation, it must be wiped again afterwards to prevent bumps and blisters. Let **JOTUN Gunning og lim for våtrom** and the wall covering dry for 12 hours. Then apply **JOTUN Gunning og lim for våtrom**. Consumption 4-5 m²/litre. Let this dry for 12 hours.

When laying fiber glass wallcoverings, use a thin knife blade with new thin blades for cutting into the fiber glass. Cutting injuries or scratches in the fiber glass cloth that occur in connection with cutting for pipe penetrations must be repaired with an extra coat of undiluted **JOTUN Gunning og lim for våtrom** over the damage.

Topcoat: 2-3 coat **JOTAPROFF AquaTech**.

Substrates previously painted with Jotuns Våtromssystem (Jotun's wet room system)

Surface preparation: Clean with **JOTUN Spesialvask før maling**, sand down and remove dust.

Topcoating: 2 coats **JOTAPROFF AquaTech**.

Maintenance

Newly painted surfaces must not be cleaned or exposed to water the first 10 days (the product's curing time). **JOTUN Spesialvask før maling** is recommended. If other detergents are used, the pH value of this must not exceed pH 9.

For daily cleaning the temperature of the wash water must be <40 °C.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste



Empty and dry pails can be sorted together with plastic packaging. The metal handle must be removed and be sorted with metallic packaging. See the QR code for more information.



Sorted as plastic



Remove the handle

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

Environmental labelling



2096 0002

The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Green Building Standards

The declared product contributes to Green Building Standard credits by meeting the following specific requirements:

- The emission requirements for M1: Classification of Indoor Environment 2018
- Swan (2096 0002)
- Property criteria in BASTA (2018:A2)
- Accepted according to Building Evaluation Assessment Criteria (Byggvarubedømmingens Bedømmingskriterier) 4.0 (2016)
- Class B according to Bedømmingskriterier (Assessment Criteria) 6.0 for SundaHus (2013)

BREEAM® NOR (2012/2016): Hea 9/02: VOC content for "Interior matt walls and ceilings" (Gloss <25@60°) (30g/l) (EU Directive 2004/42/CE) and emission demands (ISO 16000 series or CDPH v 1.2).

BREEAM® NOR (2012/2016): Mat 1.3/01: Product specific type III EPD (ISO 14025, ISO 21930, EN 15804) for Jotun A/S.

BREEAM® NOR (2012/2016): Mat 1.5/01: This product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

Additional certificates and approvals may be available on request.

Approvals



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Contact information

Jotun A/S
Box 2021, NO-3202 Sandefjord
Tel: +47 33 45 70 00

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.