

# **Jotashield Sheen (KH)**

## **Product description**

#### **Type**

A premium 100% acrylic emulsion exterior paint with AntiFade Colours that fights colour fading caused by the weather elements and delivers outstanding durability with the widest selection of colours. This product has passed TIS 2321-2549.

#### **Features and benefits**

2xUV Protected colours - Colours last two times longer than other exterior paints.

Dirt Resistance - Paint film resist dirt pick up from the environment and is easily washed off by the rain.

Reduces Temperature - Paint reflects sunlight therefore reduce the surface temperature and cools your homes or buildings.

Anti Algae & Anti Fungal - Long lasting protection against fungus and algae in tropical climates.

Water Resistant - Resist water ensuring less stain marks.

Formulated without Harmful Chemicals - Free from harmful chemicals such as APEO, formaldehyde, heavy metals and has low volatile organic compound (VOC).

#### Recommended use

For exterior application, suitable for new buildings or repainting.

#### **Substrate**

On concrete, masonry, plaster & brick work surfaces.

## **Product data**

**Packaging size** 3.785 L , 9.463 L and 18.925 L.

**Colours** As per the colour card and available in Jotun Multicolor tinting system (Exterior

range).

**Solids** 38  $\pm$  2 volume%

# **Application data**

#### **Remarks**

Handle with care. Stir well before use.

#### **Application methods**

By brush, roller, airless spray or conventional spray.

#### Guiding data for airless spray

**Nozzle tip** 0.021" - 0.027"

**Spray angle degrees** 65°-80°

Pressure at nozzle 140 - 190 kg/cm<sup>2</sup> (2100 psi)

#### **Conditions during application**

Date of issue: 04.08.2016 Product code: 35583 Page: 1/3

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.

# Technical Data Sheet Jotashield Sheen (KH)



The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

#### Spreading rate per coat

Theoretical 9,5  $m^2/l$  - 12,7  $m^2/l$ 

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

#### Recommended film thickness per coat

#### **Thinner**

Water

#### **Dilution**

The paint is ready to use after proper stirring. If thinning is required, water may be added up to a maximum of 5%.

#### **Drying times**

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

- 1. Recommended data given is, for recoating with the same generic type of paint.
- 2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
- 3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

#### Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	2 h	1 h	0.5 h
Hard dry	8 h	6 h	4 h
Dry to over coat, minimum	4 h	2 h	1 h

## **Directions for use**

#### **Surface preparation**

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

#### **Recommended paint system**

#### **Primer**

Cito Primer 09 (KH) or Jotashield Primer (KH): 1 coat

#### **Topcoat**

Date of issue: 04.08.2016 Product code: 35583 Page: 2/3

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.

# Technical Data Sheet Jotashield Sheen (KH)



Jotashield Sheen (KH): 2 coats

#### **Storage**

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## **Certificates**

Complies to Thai Green Label and Singapore Green Label.

# **Health and safety**

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## **Disclaimer**

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.