

JOTUN Panellakk

Product description

Type

Waterborne matte interior laquer.



Features and benefits

Provides an almost transparent appearance. Contains light filter which effectively reduces yellowing. Protects substrate from fat, water and others that can provide stains. Easy to apply - without dripping and spilling. Stays well in the brush. Low odor and dries quickly. **JOTUN Panellakk** is a clear base that can be used both as clear and broken in selected colors.

Recommended use

Indoor on yellowed / previously treated panel. Especially suitable for previously treated panel. Always start with a test area on similar surface to check whether the colour is as expected. Can also be used on new panel.

23°C-50% R.H.



23°C-50% R.H.



Overmalbar
Övermålningsbar



JOTUN Penselrens/
Vann

Product data

Packaging size

0,75 L (filling level 0,68 L) and 3 L (filling level 2.7 L)

Base availability

Clear.

Colors

JOTUN Panellakk can be used as clear or mixed over **Jotun Multicolor** to shades of white or selected colors. The different yellow tones of the panel will affect the final color. The correct color is determined after drying.

Gloss level

Matt

Solids by volume

29 ± 2 volume%

Specific gravity

1.11

pH value

8.5 to 9.5

VOC for Ready-for-Use Mixture

EU limit value for the product (cat. A/e): 130 g/l. The product contains max 65 g/l VOC.

Application data

Remarks

Stir well. Contents of tins with different production numbers should be mixed.

Application equipment / methods

Flat, dense brush.

Cleaning of painting tools

JOTUN Penselrens and water.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	10 - 12	83 - 100	24 - 29

Conditions during application

Air and surface temperature must be above +10 °C during application.

Cleaning of spillage

JOTUN Spesial wipes are recommended to clean spillage. JOTUN Spesial wipes are a convenient washing/cleansing wipe for use before and during paint work.

Drying times

Drying times deviate because of changes in temperature, air humidity, air circulation and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Surface (touch) dry	1 h
Recoatable, minimum	2 h

Directions for use

Substrate	Treatment
Yellowed untreated panel / woodwork (pine / spruce):	Clean with JOTUN Spesialrens gulnet panel according to the instructions. Make sure the woodwork is dry before further processing. Lightly sand with abrasive paper. Remove dust from sanding. Perform a test application to see if the color is the one desires. Apply JOTUN Panellakk on 1-2 panel boards throughout the panel length. Two coats provide better protection against yellowing and provides greater color effect.

Previously treated panel /
woodwork (pine / spruce):

Wash with **JOTUN Spesialvask før maling** according to instructions. Make sure the woodwork is dry before further processing. Lightly sand with abrasive paper. Remove dust from sanding. Perform a test application to see if the color is the one desired.
Apply **JOTUN Panellakk** on 1–2 panel boards throughout the panel length. Two coats provide better protection against yellowing and provides greater color effect.

Maintenance

Newly painted surfaces must not be cleaned the first four weeks (the product's curing time). If cleaning is necessary, the pH of the detergent must not exceed pH 9. **JOTUN Spesialvask før maling** is recommended. For daily cleaning the temperature of the wash water must be <40 °C.

Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste



Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

52949884, 52949892

NOBB module number

42093759

Contact information

Jotun A/S
P.O.Box 2021
3202 Sandefjord
Tel: 33 45 70 00

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.