

## LADY Pure Nature White

### Product description

#### Type

Water-borne oil stain for interior use.

#### Features and benefits

Gives a naturally beautiful finish that will enhance the woodwork. Contains light filter which effectively reduces yellowing. Easy to apply.

#### Recommended use

Light, untreated wood of spruce and pine. Not recommended for hard wood, such as oak.

### Product data

<b>Packaging size</b>	0,75 L (contents 0,68 L) and 3 L (content 2.7 L)
<b>Colors</b>	The surface original colour, absorbency, number of coats and application technique affects the colour appearance.
<b>Solids by volume</b>	20 ± 2 volume%
<b>Specific gravity</b>	1.08
<b>pH value</b>	8
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/e): 130 g/l. The product contains max 130 g/l VOC.

### Application data

#### Remarks

Contents of tins with different production numbers should be mixed. Stir well. Do not spray.

#### Application equipment / methods

Flat, dense, soft brush or primer brush.

#### Cleaning of painting tools

Water and **JOTUN Penselrens**.

#### Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Recommended film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended:</b>	10 - 12	83 - 100	17 - 20

## Conditions during application

Air and surface temperature must be above +10 °C during application.

## Drying times

Drying time deviates at changes in temperature, air humidity, air circulation and film thickness.

### The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Surface (touch) dry	2 h
Paintable	24 h
Fully cured	4 weeks

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry.  
Yellowed paneling must be cleaned with **JOTUN Spesialrens gulnet panel**, 1:10. Observe use instructions.  
Sand lightly and remove the dust.

### Pretreatment

Moisten new wood that does not have to be washed, with water and allow this to dry for a few hours. Lightly sand with abrasive paper. Remove dust from sanding.  
In case of remains of old surface treatment, remove this down to bare, porous wood.

### Topcoat

1-2 coats **LADY Pure Nature White**. Apply thin coats. Stain maximum 1-2 panel boards at a time in full length. Smooth the stain across the entire panel length, so that it is distributed evenly over the entire width.

### Cleaning of spillage

**JOTUN Spesial wipes** is recommended to clean spillage. **JOTUN Spesial wipes** is a convenient washing/cleansing wipe for use before and during paint work.

### Maintenance

Stained surfaces must not be cleaned the first four weeks. If cleaning is necessary, the pH of the detergent must not exceed pH 9. **JOTUN Spesialvask for maling** is recommended. For daily cleaning the suds temperature must be <40 °C.

### Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

---

## Miscellaneous

### Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.