

## JOTAPROFF Täckande Utegrund

### Product description

#### Type

Oil based opaque primer for previously painted wooden facades outdoors. To be treated with opaque stain or paint.

#### Features and benefits

Particularly developed for priming when re-painting facades with patchy scraping to bare wood. Provides good adhesion. Prolongs the durability of the paint system. The primer dries quickly.

#### Recommended use

To be applied to previously stained, opaque stained or painted woodwork.

### Product data

<b>Packaging size</b>	3 L and 10 L.
<b>Colors</b>	White.
<b>Gloss level</b>	5-10.
<b>Generic type</b>	Primer, based on special alkyd oils.
<b>Solids by volume</b>	43 ± 2 volume%
<b>Specific gravity</b>	1.36 White.
<b>pH value</b>	7
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 75 g/l VOC.

### Application data

#### Remarks

Contents of tins with different production numbers should be mixed to avoid possible colour deviations. Stir well before use.

Coating on fire protected cladding may cause salt precipitation/flaking.

Surfaces previously treated with linseed oil stain or linseed oil paints. must be cleaned to bare woodwork, because old linseed oil may cause blistering when coated with stain, translucent stain or paint. Linseed oil treated wood, which has been sanded/scraped down to bare wood, should be washed with alkaline detergent to soak and remove excess linseed oil, to reduce the risk of blistering when overcoated.

Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Perform a test application.

Sun on semi-dry treatment may cause skin drying and sun blisters.

Condensation may cause dull patches. Dull patches may also occur when drying during high relative humidity and low temperatures.

Remember to coat end grain.

### Application equipment / methods

Brush, roller or spray. Spraying: For professional application only.

### Guiding data for airless spray

Nozzle tip	0.46-0.53 mm (0.018-0.021")
Spray angle degrees	65-80°
Pressure at nozzle	15-18 MPa (150-180 kg/cm <sup>2</sup> )

### Cleaning of painting tools

Water and JOTUN Penselrens.

### Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended, previously treated sawn wood:	4 - 7	143 - 250	61 - 108
Recommended, previously treated planed wood :	5 - 8	125 - 200	54 - 86

### Dilution

Please note! Can not be mixed with other paint products. Do not mix in oil additives.

### Conditions during application

Air and surface temperature must be above +5 °C during application. Do not paint if there is a risk of condensation or rain until the film is dry.

### Drying times

Drying time deviates at changes in temperature, air humidity, wind, absorption and film thickness. Lower temperature will extend the drying times.

#### The drying time is measured by stated values:

Relative Humidity (RH)	50 %	50 %	50 %
Air temperature	5 °C	15 °C	23 °C
Substrate temperature	5 °C	15 °C	23 °C

Dust dry	8 h	6 h	4 h
Recoatable, minimum	16 h	12 h	6 h

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry. Sand down sharp edges.

Previously treated wood should be cleaned using JOTUN 2-i-1 Kraftvask og soppfjerner / JOTUN 2-i-1 Kraftvask och mögeldesinfektion / JOTUN 2-i-1 Kraftvask/Træ- og Murrens. Remove loose paint/stain and wood fibres by wire brush or scraping. Sand glossy and hard surfaces.

Contaminated/fungus infested surfaces to be washed with JOTUN 2-i-1 Kraftvask og soppfjerner /- och mögeldesinfektion /- Træ- og Murrens.

### Primer

Before or immediately after installation of new woodwork, treat with a brush coat of **VISIR Oljegrunning pigmentert**. Apply 3-4 coats **VISIR Oljegrunning pigmentert** wet-on-wet to the end grains/cut surfaces. Previously painted surfaces must be treated with one coat of **JOTAPROFF Täckande Utegrund**. Recoat with required finishing coats within 1 month.

### Topcoat

Can be treated with all Jotun's opaque stains and paints. Finish with two coats of the selected topcoat. Follow the instructions for the selected product.

### Remarks

See also Jotun's website: [jotun.com](http://jotun.com).

### Maintenance

### Storage

In storage and in transport keep the container frost free and upright.

### Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet. First-aid measures, refer to section 4. Handling and storage, refer to section 7. Transport information, refer to section 14. Regulatory information, refer to section 15.

### Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.