

SeaQuest Tiecoat

Product description

This is a three component elastomeric silicone tie coat. It provides excellent adhesion for Jotun FRC Topcoat. Can be applied directly onto the following primers:
Jotacote Universal N10
Jotacote HF002
Jotaprime 500 Alu / Alu RT
Jotaprime 510
Penguard Universal

Typical use

Marine:
Recommended for under water hull in newbuilding and drydocking. Specially designed as a tie coat for Jotun FRC Topcoats, ensuring a relatively long over coating interval giving flexibility in production.

Colors

light red

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	55 ± 2 %
Flash point	ISO 3679 Method 1	75 °F (24 °C)
Density	calculated	1 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested) (CARB(SCM)2007, SCAQMD rule 1113, Hong Kong)	3.33 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color. All data is valid for mixed paint.

Film thickness per coat

Typical recommended specification range

Dry film thickness	4 mils (90 µm)
Wet film thickness	6 mils (160 µm)
Theoretical spreading rate	250 ft ² /gal (6.1 m ² /l)

Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Application

Application methods

The product can be applied by

Spray: Use airless spray.

Care should be taken to avoid overspray onto other areas.

Product mixing ratio (by volume)

SeaQuest Tiecoat Comp A	16.7 part(s)
SeaQuest Tiecoat Comp B	0.6 part(s)
SeaQuest Tiecoat Comp C	0.9 part(s)

Thinner/Cleaning solvent

Do not add thinner.

Cleaning solvent: Jotun Thinner No. 7

Guiding data for airless spray

Nozzle tip (inch/1000):	15-21
Pressure at nozzle (minimum):	210 bar/3000 psi

Drying and Curing time

Temperatures:

-10°C = 14°F / -5°C = 23°F / 0°C = 32°F / 5°C = 41°F / 10°C = 50°F / 15°C = 59°F / 23°C = 73°F / 35°C = 95°F / 40°C = 104°F / 100°C = 212°F

Substrate temperature	10 °C	15 °C	23 °C	40 °C
Surface (touch) dry	8 h	6 h	4 h	2 h
Dried to over coat, minimum	18 h	16 h	12 h	6 h

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

After finished application the substrate temperature must be kept at minimum 50 °F (10 °C) for at least 2 hours. Lowest substrate temperature during the drying/curing period is 41 °F (5 °C).

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and above 30 %, and at average of the DFT range for the product.

Note: The cured product will reveal some tackiness.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Induction time and Pot life

Temperatures: 15°C = 59°F / 23°C = 73°F

Paint temperature	10 °C	15 °C	23 °C	40 °C
Pot life	1 h	1 h	1 h	30 min

Recommended type of primer

Can be applied directly onto the following primers:

Jotacote Universal N10

Jotacote HF002

Jotaprime 500 Alu / Alu RT

Jotaprime 510

Penguard Universal

Packaging (typical)

	Volume (liters)	Size of containers (liters)
SeaQuest Tiecoat Comp A	16.7	20
SeaQuest Tiecoat Comp B	0.6	0.75
SeaQuest Tiecoat Comp C	0.9	1

0.6 l = 0.16 gal

0.9 l = 0.24 gal

16.7 l = 4.41 gal

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C)

SeaQuest Tiecoat Comp A	18 month(s)
SeaQuest Tiecoat Comp B	18 month(s)
SeaQuest Tiecoat Comp C	18 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., and application quality. Contact your local Jotun office for further information.

Disclaimer

Technical Data Sheet

SeaQuest Tiecoat



Jotun Protects Property

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
