

## JOTUN Fargeprøve Eksteriør (2019)

### Product description

#### Type

Opaque colour swatch for outdoor use on wood.

#### Features and benefits

**JOTUN Fargeprøve Eksteriør (2019)** gives you the confidence that you choose the right color.

#### Recommended use

To be applied to new, previously stained or painted woodwork, as well as impregnated. To be used in combination with **VISIR Oljegrunning**, as part of a system treatment. Also suitable as a topcoat for previously primed gutters, fascias made of plastic and metal commonly use on buildings. Prime the metal with **QUICK Bengalack Metallgrunning**.

### Product data

<b>Packaging size</b>	0.5 L (filling level 0.45 L)
<b>Base availability</b>	White, A-, B-, C-, oxide red-, ochre- and yellow base. Bases must not be used unless tinted (does not apply for white base).
<b>Tinting</b>	Bases must be tinted using <b>Jotun Multicolor</b> .
<b>Colors</b>	White base may be used untinted as White.
<b>Gloss level</b>	20-30
<b>Generic type</b>	Based on special acrylic and alkyd.
<b>Solids by volume</b>	35 ± 2 volume% White base.
<b>Specific gravity</b>	1.27 White base.
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 80 g/l VOC.

### Application data

#### Remarks

Contents of tins with different production numbers should be mixed. Stir well before use. Coating on fire protected cladding may cause salt precipitation/flaking. Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Perform a test application. Sun on semi-dry paint may cause skin drying and sun blisters. Please be aware of linseed oil/moisture problems. Condensation may cause dull patches.

#### Application equipment / methods

Brush or roller.

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended, sawn wood:</b>	7 - 10	100 - 143	35 - 50
<b>Recommended, planed wood:</b>	10 - 12	83 - 100	29 - 35

### Thinner

Shall not be thinned.

### Dilution

Do not mix in oil additives.

### Conditions during application

Air and surface temperature must be above +5 °C during application. Do not paint if there is a risk of condensation or rain until the film is dry.

To ensure long durability it is important to apply a sufficient amount on edges and planed surfaces. Min. 3 coats (100 µm dry paint film).

### Drying times

The drying time depends on the surface temperature (min. +5 °C), absorption, humidity and air circulation.

#### The drying time is measured by stated values:

Relative Humidity (RH)	50 %	50 %	50 %
Air temperature	5 °C	10 °C	23 °C
Substrate temperature	5 °C	10 °C	23 °C

Dust dry	1.5 h	1 h	0.5 h
Paintable	6 h	3 h	2 h

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry. For the best possible edge coverage, sand down sharp edges. Fresh wood left untreated for more than 4 weeks should be cleaned using **JOTUN 2-i-1 Husvask og soppfjerner** / **JOTUN 2-i-1 Husvask och mögeldesinfektion** / **JOTUN 2-i-1 Husvask/Træ- og Murrens** and brushed with a wire brush.

Previously treated wood should be cleaned using **JOTUN 2-i-1 Kraftvask og soppfjerner** / **JOTUN 2-i-1 Kraftvask och mögeldesinfektion** / **JOTUN 2-i-1 Kraftvask/Træ- og Murrens**. Remove loose paint and wood fibres by wire brush or scraping. Sand glossy and hard surfaces.

### Primer

Apply **VISIR Oljegrunning** to bare woodwork. The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces.

Use **VISIR Oljegrunning klar** when treated during the cold season.

### Topcoat

**JOTUN Fargeprøve Eksteriør (2019)**. New, planed woodwork: 3 coats. Previously treated or new, unplanned/rough woodwork: 2 coats.

### Cleaning of spillage

Water and **JOTUN Penselrens**.

### Storage

In storage and in transport keep the container frost free and upright.

### Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## Miscellaneous

### Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.