

QUICK Bengalack Effekt Spray

Product description

Type

QUICK Bengalack Effekt Spray is alkyd-based spray paint with metallic effect.

Features and benefits

QUICK Bengalack Effekt Spray provides a brilliant metallic effect. **QUICK Bengalack Effekt Spray** silver, gold and copper are opaque paints. Silver transparent is used as topcoat over non-metallic colors.

Recommended use

QUICK Bengalack Effekt Spray is for use indoors and outdoors on metal, wood and hard plastics. Used on objects such as bicycles, furnishings, fixtures and ornaments such as vases, candlesticks and the like.

Product data

| | |
|--------------------------------------|---|
| Packaging size | Spray can (net content about 400 ml). |
| Colors | Glossy: 160 Silver Metallic, 170 Gold Metallic, 180 Copper Metallic, 260 Transparent Silver |
| Gloss level | Glossy: 90–100 |
| VOC for Ready-for-Use Mixture | EU limit value for the product (cat. B/e): 840 g/l. The product contains max 840 g/l VOC. |

Application data

Propellant: Butane/propane.
The product is classified as extremely flammable.

Application equipment / methods

Shake vigorously for 2 min. before use. Apply evenly to the desired appearance.

Keep the box as vertical as possible during spraying. Spray evenly and thinly at a distance of approx. 30–40 cm. Keep the can in motion during application. First spray in horizontal direction. After 5 min., spray in vertical direction. Repeat with approx. 5 min. intervals until desired effect. Finish with a full coat.

After use, turn the box upside down and spray until only propellant gas comes out.

Thinner

White Spirit.

Conditions during application

Do not spray if there is a risk of condensation or rain and wait until the film is dry.

Drying times

The drying time is affected by temperature, air humidity and film thickness.

| | |
|-------------------------------|--------------|
| Relative Humidity (RH) | 50 % |
| Air temperature | 23 °C |
| Substrate temperature | 23 °C |
| Recoatable, minimum | Ca 5 minutes |
| Dry to use | Min. 1 hour |
| Fully cured | 3–4 weeks |

Directions for use

| Substrate | Treatment |
|------------------------------------|--|
| New iron and steel: | Degrease with UNIVERSALTYNNER NR. 1 or QUICK Bengalack Avfetting Spray . Wash with BUTINOX Husvask og Kraftvask (diluted with water 1:10). Rinse with water. The substrate must be completely dry before further treatment. Then, prime with QUICK Bengalack Grunning . Topcoat: QUICK Bengalack Effekt Spray . |
| Previously painted iron and steel: | Remove all rust, loose paint, grease and other contaminants. Existing paint should be sanded. Wash with BUTINOX Husvask og Kraftvask (diluted with water 1:10). Rinse with water. The substrate must be completely dry before further treatment. Then, prime with QUICK Bengalack Grunning . Topcoat: QUICK Bengalack Effekt Spray . |
| Galvanised steel and light metals: | Degrease with QUICK Bengalack Avfetting Spray or UNIVERSALTYNNER NR. 1 . Wash with BUTINOX Husvask og Kraftvask diluted 1:5 with water. RINSE THOROUGHLY with fresh water! The substrate must be completely dry before further treatment. Then, prime with QUICK Bengalack Grunning . Topcoat: QUICK Bengalack Effekt Spray . |
| Hard plastics: | The substrate shall be free from grease and other contaminants. Wash with BUTINOX Husvask og Kraftvask . Rinse with water. The substrate must be completely dry before further treatment. Then, prime with QUICK Bengalack Grunning . Topcoat: QUICK Bengalack Effekt Spray . |

Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container upright. Can be stored in freezing temperatures.

Disposal of waste

Empty containers and residues of contents are delivered to municipal waste disposal or nearest environmental station.



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

Contact information

Jotun Sverige AB
Box 151
421 22 Västra Frölunda
Tlf.: 031 69 63 00

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.