

## Hardtop WT8

### Product description

This is a two component chemically curing polyurethane coating. It has a semi gloss finish with very good gloss retention. It has good chemical resistance. It is a high solids product.

### Typical use

Protective:  
Recommended for wind turbine towers. Suitable for a wide range of industrial structures.

### Colors

light grey

### Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	62 ± 2 %
Gloss level (GU 60 °)	ISO 2813	semi gloss (55-70)
Flash point	ISO 3679 Method 1	82 °F (28 °C)
Density	calculated	1.4 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	2.74 lbs/gal

The provided data is typical for factory produced products, subject to slight variation depending on color.  
Gloss description: According to Jotun Performance Coatings' definition.

### Film thickness per coat

#### Typical recommended specification range

Dry film thickness	2 mils (50 µm)	4 mils (100 µm)
Wet film thickness	3 mils (80 µm)	6 mils (160 µm)
Theoretical spreading rate	510 ft <sup>2</sup> /gal (12.4 m <sup>2</sup> /l)	250 ft <sup>2</sup> /gal (6.2 m <sup>2</sup> /l)

## Surface preparation

### Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

## Application

### Application methods

The product can be applied by

- Spray: Use air spray or airless spray.
- Brush: Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
- Roller: May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

### Product mixing ratio (by volume)

Hardtop WT8 Comp A	5 part(s)
Hardtop WT8 Comp B	1 part(s)

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 7 / Jotun Thinner No. 10  
Jotun Thinner No. 68

Jotun Thinner No 68 can be used for longer open time and less dry spray during application in warm conditions. Recommended maximum addition is 10% (on volume) in ready mixed paint.

Jotun Thinner No. 63 can be used to reduce the drying time if required. Recommended maximum addition is 5 % (on volume) in ready mixed paint.

Note that the pot life will be reduced when adding the thinner.

### Guiding data for airless spray

Nozzle tip (inch/1000):	13-19
Pressure at nozzle (minimum):	150 bar/2100 psi

### Guiding data for air spray

Nozzle tip:	Gravity gun: 1.6-1.8 (mm) / Pressure pot: 1.4-1.6 (mm)
Pressure at nozzle (minimum):	Gravity gun: 3.2 bar / Pressure pot: 3.2 bar
Pressure at pressure pot:	1.6 bar

## Drying and Curing time

Temperatures:

-10°C = 14°F / -5°C = 23°F / 0°C = 32°F / 5°C = 41°F / 10°C = 50°F / 15°C = 59°F / 23°C = 73°F / 35°C = 95°F / 40°C = 104°F / 100°C = 212°F

Substrate temperature	32 °F	41 °F	50 °F	73 °F	104 °F
Surface (touch) dry	4 h	3 h	2 h	1 h	1 h
Walk-on-dry	40 h	24 h	16 h	8 h	4 h
Dried to over coat, minimum	24 h	18 h	10 h	5 h	3 h
Dried/cured for service	20 d	14 d	10 d	5 d	3 d

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Induction time and Pot life

Temperatures: 15°C = 59°F / 23°C = 73°F

Paint temperature	73 °F
Pot life	1.5 h

## Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	140 °C

Resistant to spills of most oils, aliphatic petroleum products and non aggressive chemicals.

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

## Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy, zinc epoxy, epoxy mastic, polyurethane

Subsequent coat: polyurethane

## Packaging (typical)

	Volume (liters)	Size of containers (liters)
Hardtop WT8 Comp A	16.7	20
Hardtop WT8 Comp B	3.3	5

The volume stated is for factory made colors. Note that local variants in pack size and filled volumes can vary due to local regulations.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

## Shelf life at 73°F (23 °C)

Hardtop WT8 Comp A	48 month(s)
Hardtop WT8 Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

## Note

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

---

## Color variation

When applicable, products primarily meant for use as primers or antifoulings may have slight color variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Color and gloss retention on topcoats/finish coats may vary depending on type of color, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---