

Guard Style TE D

PRODUCT DESCRIPTION

Guard Style TE D is a range of powder coatings specifically developed to provide improved efficiency in powder consumption, with good appearance and effect stability in mind. The powder is available in wide range of colours with a smooth and fine texture finish in medium and high gloss. The product meets the industry standard with regard to mechanical and chemical properties. Please contact your local sales representative for more information.

Application areas

This product is recommended for interior use on surfaces exposed to a dry environment.

Typical application areas:

- Shop fittings
- Industrial racking systems
- Refrigerators
- Indoor furniture
- Interior lighting
- Steel doors
- Elevator doors
- Machinery enclosures
- Safe box
- Power tools

POWDER PROPERTIES

Property	Standard	Result
Specific gravity	Calculated	Typically 1.60 ± 0.20 g/cm ³

Storage

Keep in a dry cool area. When stored at a maximum 25 °C (77 °F) and maximum relative humidity 60%, a shelf life of 12 months is obtained from the date of manufacture. It is recommended to re-evaluate product performance after this period.

APPLICATION

Pretreatment

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the pretreatment. For optimal results, it is recommended to follow the pretreatment supplier's instructions and recommendations.

Powder application

Curing schedule	Object temperature	Time
Guard Style TE D0	200 °C	10 minutes
Guard Style TE D8	180 °C	10 minutes
Guard Style TE D6	160 °C	10 minutes

Recommended film thickness (µm): > 50

Equipment

Suitable for Corona charging equipment.

APPEARANCE

Colour	White and light colours.	
Gloss	EN ISO 2813 (60°)	
	D0	55-89
	D8	45-89
	D6	45-89
Finish	Suitable for Smooth and Fine Texture	

If the significant surface is too small or unsuitable for the gloss to be measured with the glossmeter, the gloss should be compared visually with the reference sample (from the same viewing angle).

Other gloss levels are available upon technical approval.

PERFORMANCE

The technical data provided below are typical for this product when applied as follows:

Substrate	Iron-phosphated cold rolled steel
Substrate thickness (mm)	0.8
Film thickness (µm)	50-80

Typical values when tested.

Property	Standard	Result
Adhesion	ISO 2409	Cross-cut rating Gt0 (100 % adhesion)
Cupping test	ISO 1520	≥ 5 mm
Impact resistance	ASTM D2794 (5/8 " ball) (inch-pounds, front and reverse) D0: 45-60 D8: 60-95 Fine Texture	60/40 100/80 40/20
Resistance to neutral salt spray	ISO 9227 ISO 4628-2 ISO 4628-8	No blistering and maximum 1 mm corrosion creep from scribe after 240 hours
Resistance to humid atmospheres	ISO 6270-2 ISO 4628-2 ISO 4628-8	No blistering, maximum 2 mm corrosion creep from scribe after 504 hours

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

Technical Data Sheet

Guard Style TE D

