

SeaQuantum Skate

Product description

This is a one component state of the art chemically hydrolysing silyl methacrylate antifouling coating. It is specially designed to work together with Jotun HullSkater, enduring repeated mechanical contact with the brush without erosion of the coating due to proactive cleaning. The product provides superior fouling protection, ultra low friction and market leading hull performance as part of Jotun Hull Skating Solutions.

Application of this product shall follow the instructions in **Application Guide (AG) for SeaQuantum Skate**. For further advice please contact your local Jotun office.

Typical use

Marine:

Recommended for underwater hull in newbuilding and drydocking. Designed as an ultra premium solution for vessels with main focus on long term hull performance and fuel saving. The product is designed for long service periods and can be used up to 90 months as a part of a complete coating system.

Typical trade

Designed for both global and coastal trade. Recommended for exposure to both sea and fresh water during newbuilding outfitting.

Approvals and certificates

Compliant with IMO Antifouling System Convention AFS/CONF/26 + IMO MEPC.331(76).

Additional certificates and approvals may be available on request.

Colours

dark red, light red

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	55 ± 2 %
Flash point	ISO 3679 Method 1	25 °C
Density	calculated	1.9 kg/l

Region	Regulation	Test Standard	VOC Value
US	CARB(SCM)2020 / SCAQMD rule 1113	Calculated	415 g/l
Hong Kong	Air Pollution Control (VOC) Regulation	Calculated	415 g/l
EU	European Paint Directive 2004/42/CE	Calculated	415 g/l
EU IED	Industrial Emission Directive 2010/75/EU	Calculated	415 g/l
Korea	Korea Clean Air Conservation Act	Calculated	415 g/l

China GB 30981-2020 Limit of harmful substances of industrial protective coatings GB/T 23985-2009 8.3 393 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.

Film thickness per coat

Typical recommended specification range

Dry film thickness 75 - 175 μm
Wet film thickness 135 - 320 μm
Theoretical spreading rate 7.3 - 3.1 m^2/l

Max total DFT for multiple coats in the antifouling system: 600 μm

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Coated surfaces	New tie coat or new antifouling: Remove any contamination that could interfere with the intercoat adhesion. Exceeding maximum recoat intervals will require cleaning/abrading and/or application of additional coats, depending on condition. Aged antifouling with leached layer: Removal by thorough fresh water washing at minimum nozzle pressure 200 bar.	New tie coat or new antifouling: Remove any contamination that could interfere with the intercoat adhesion. Exceeding maximum recoat intervals will require cleaning/abrading and/or application of additional coats, depending on condition. Aged antifouling with leached layer: Removal by thorough fresh water washing at minimum nozzle pressure 340 bar.

Application

Application methods

The product can be applied by

Spray: Use airless spray.
Brush: May be used. Care must be taken to achieve the specified dry film thickness.

Roller: May be used. Care must be taken to achieve the specified dry film thickness.

Product mixing

Single pack

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 7

Guiding data for airless spray

Nozzle tip (inch/1000): 21-31
Pressure at nozzle (minimum): 150 bar / 2100 psi

Drying and Curing time

Substrate temperature	-10 °C	0 °C	10 °C	23 °C	40 °C
Surface (touch) dry	8 h	2 h	45 min	30 min	30 min
Dry to over coat, minimum	27 h	16 h	9 h	7 h	6 h
Dried/cured for immersion	39 h	24 h	10 h	9 h	8 h

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

The dried/cured for immersion data in the above table is the time required until the product is ready for sailing. For mechanical resistance to fenders and similar equipment longer drying times may be required. Please consult the Application Procedure for further advice.

When high film thickness is applied the antifouling will stay soft longer. To enable hull roughness reading when two or more antifouling coats are applied in rapid succession it is recommended to double the minimum time for immersion.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for immersion: Minimum time before the coating can be permanently immersed in sea water.

Recommended type of primer

Anticorrosive primer system suitable for purpose. Recommended tie coat for the subsequent antifouling coat is:
Safeguard Universal ES
or
Safeguard Plus

Packaging (typical)

	Volume (litres)	Size of containers (litres)
SeaQuantum Skate	20	20

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, shaded, cool, well-ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Storage temperature not to exceed 35 °C.

Shelf life at 23 °C

SeaQuantum Skate 9 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
