

QUICK Bengalack Varmebestandig Spray

Product description

Type

QUICK Bengalack Varmebestandig Spray is an alkyd paint.

Features and benefits

QUICK Bengalack Varmebestandig Spray can withstand up to 650 ° C. Renewes and maintains. Available in black matt.

Recommended use

QUICK Bengalack Varmebestandig Spray is designed for surfaces exposed to heat: wood stoves, fireplaces, exhausts, barbecues and the like.

Product data

Colours	Black.
Gloss level	Matt.
Flash point	Closed cup: -7°C (19.4°F)
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. B/e): 840 g/l. The product contains max 840 g/l VOC.

Application data

Propellant: Butane/propane.
The product is classified as extremely flammable.

Application equipment / methods

Shake vigorously for 2 min. before use. Apply evenly in recommended film thickness. Keep the box as vertical as possible during spraying. Spray evenly and thinly at a distance of approx. 30–40 cm. Keep the can in motion during application. First spray in horizontal direction. After 5 min., spray in vertical direction. Repeat with approx. 5 min. intervals until desired effect. Finish with a full coat. After use, turn the box upside down and spray until only propellant gas comes out.

Thinner

White Spirit.

Conditions during application

Do not spray if there is a risk of condensation or rain and wait until the film is dry.

Drying times

The drying time is affected by temperature, air humidity and film thickness.

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C
Recoatable, minimum	Ca 5 minutes
Dry to use	Min. 30 minutes
Fully cured	3-4 weeks

Directions for use

The substrate must be clean, sound and dry.

Substrate	Treatment
New iron and steel:	Degrease with QUICK Bengalack Avfetting Spray or UNIVERSALTYNNER NR. 1 . Wash with BUTINOX Husvask og Kraftvask (diluted with water 1:10). Rinse with water. The substrate must be completely dry before further treatment. Then treatment with QUICK Bengalack Varmebestandig Spray .
Previously painted iron and steel:	Remove all rust, loose paint, grease and other contaminants. Existing paint should be sanded. Wash with BUTINOX Husvask og Kraftvask (diluted with water 1:10). Rinse with water. The substrate must be completely dry before further treatment. Then treatment with QUICK Bengalack Varmebestandig Spray .
Galvanised steel and light metals:	Degrease with QUICK Bengalack Avfetting Spray or UNIVERSALTYNNER NR. 1 . Wash with BUTINOX Husvask og Kraftvask diluted 1:5 with water. Rinse thoroughly with fresh water. The substrate must be completely dry before further treatment. Then treatment with QUICK Bengalack Varmebestandig Spray .

Management, Operation and Maintenance

N/A

Storage

Can be stored in freezing temperatures. In storage and in transport keep the container upright.

Disposal of waste

Empty containers and residues of contents are delivered to municipal waste disposal or nearest environmental station.



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: 4242569

Safety rules	
5-3	1993

Miscellaneous

Contact information

Jotun Danmark A/S
 Jernet 6
 6000 Kolding

Tel: +45 76 30 32 00
 mail@jotun.dk

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.