

## Jotashield TileGlo

### Product description

#### Type

This product is a exterior water based paint based on pure acrylic emulsion which offers excellent long lasting sheen and colour.

#### Features and benefits

Unlike other roof tile paints available, this product has superior formulation which gives exterior tiles a long-lasting rich sheen, protection against algae, cracking and peeling. The unique UV protected colours offer outstanding protection against destructive effect of UV rays present in sunlight, assuring the colours of your roof tile will remain vibrant and lustrous for a long time. Specially designed to withstand the harsh weather conditions and provides durable & long lasting semigloss finish with low dirt pick up.

#### Recommended use

Roof tiles and non porous baked clay tiles.

#### Substrate

Roof tiles and non porous baked clay tiles.

Substrate should have sufficient strength to receive the paint. Any defects in the substrate like surface undulations, cracks, pin holes etc., should be rectified/filled before starting painting. The compatibility of any third party filling material, if used, shall be confirmed with Jotun before application.

### Product data

<b>Packaging size</b>	1 L , 4 L and 20 L
<b>Colours</b>	White and Colours available in Jotun Multicolor system.
<b>Solids by volume</b>	33 ± 2 volume% Theoretical
<b>Specific gravity</b>	1.12 Theoretical
<b>VOC</b>	15 g/l ISO 11890 EU

### Application data

#### Remarks

Handle with care. Stir well before use.

#### The product can be applied by

Spray : Airless spray or Conventional spray.

Brush : Recommended to paint corners and edges.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.021-0.027"
<b>Spray angle degrees</b>	65-80°
<b>Pressure at nozzle</b>	140 - 190 kg/cm <sup>2</sup> (2100 psi)

### Film thickness per coat

#### Typical recommended range

Dry film thickness 27 - 37  $\mu\text{m}$

Wet film thickness 62 - 77  $\mu\text{m}$

Film thickness will vary and are calculated as an average.

Theoretical spreading rate 10.2 - 8.4  $\text{m}^2/\text{l}$

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

Maximum spread rate per coat is obtained at minimum dry film thickness and vice versa.

### Thinner

Water

### Dilution

Maximum 30 %

### Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

### Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

#### The drying time is measured by stated values:

##### Relative Humidity (RH) 50 %

Substrate temperature	10 °C	23 °C	40 °C
Surface (touch) dry	12 h	6 h	2 h
Hard dry	16 h	8 h	4 h
Dry to over coat, minimum	12 h	6 h	2 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

**In case of excessive chalky and repainting of surface; use Acrylic Emulsion Primer (1 coat) prior to application.** Growth of fungus, algae or moss should be removed by wire brushing and water. In case of dents and holes use Jotun Cement Putty. Jotashield TileGlo should not be applied on surfaces / substrates that are subjected to continuous seepage or dampness.

**Jotashield TileGlo should not be applied on surfaces / substrates that are subjected to continuous seepage or dampness.**

### Recommended paint system

## Topcoat

Jotashield TileGlo : 2 coats

For best results, it is advisable to apply Jotashield TileGlo on both sides of a roof tile individually before laying.

## Remarks

Other systems may be specified, depending on area of use.

Contents of packaging with different batch numbers must be mixed together before use.

Please refer to the Decorative Sales Department for technical advice.

## Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

---

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.