

## DEMIDEKK Infinity Details

### Product description

#### Type

Opaque wood protection for outdoor use with unique INFINITY technology.



#### Features and benefits

INFINITY technology provides superior protection and the product has superior color and gloss durability, which makes the surface look freshly painted for a very long time. The paint is self-cleaning. The product has a fast drying time - rainproof after one hour, and superb application properties that are specially adapted for painting windows, doors, garage doors, garden furniture and fences.

#### Recommended use

Especially suitable for planed wood, like windows, doors, window dressings, garden furniture, garage door, fences etc. To be applied to new, previously stained or painted woodwork, as well as impregnated. Also suitable as a topcoat for previously primed gutters, fascia's made of plastic and metal commonly use on buildings.



JOTUN 3-i-1 Kraftvask och mögeldesinfektion



Vatten/  
JOTUN Penseltvätt

### Product data

<b>Packaging size</b>	0,75 L (filling level 0,68 L) and 3 L (filling level 2.7 L)
<b>Base availability</b>	White, A, B, C and oxide red.
<b>Tinting</b>	Bases must be tinted using <b>Jotun Multicolor</b> .
<b>Gloss level</b>	40-50 semi gloss
<b>Generic type</b>	Based on the INFINITY technology and the AMA (Alkyd Modified Acrylics) technology.
<b>Solids by volume</b>	38 ± 2 volume%
<b>Specific gravity</b>	1.05 - 1.24 C-base / white base
<b>pH value</b>	8 to 9
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 75 g/l VOC.

### Application data

#### Remarks

To ensure long durability it is important to apply a sufficient amount of paint on edges and planed surfaces, min. 3 coats (100 µm dry paint film).

Sand down sharp edges. Saturate all end grains/cut surfaces thoroughly, apply 3-4 coats wet-on-wet. Perform a test application.

Can not be mixed with other paint products and do not mix in oil additives.

Stir well both before and during use.

Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Linseed oil / oils in the substrate can cause blisters and flaking. Sun on semi-dry treatment may cause skin drying and sun blisters. Painting on fire protected cladding may cause salt precipitation/flaking.

Bases must be tinted using **Jotun Multicolor**. Content of cans from different productions and different tinting systems may cause shade differences. Measures one can take to avoid colour differences:

- Mix different production numbers together. Stir well.  
The production number can be found after the letters SZ or SV on the label in the front of the can.
- It is advantageous to use the same batch number within the same defined area.  
Changing the can in the middle of the wall or confined area, increases the possibility of a visible colour difference.
- There may be colour differences of paint which are mixed on different tinting machines and / or at different times. Please be aware of this if you need to buy more paint / opaque stain / stain for the same project at a later time.
- If you notice any visible differences, contact your point of sale or Jotun Technical Service (tel. 33457530).

### Application equipment / methods

Brush, roller or spray.

### Guiding data for airless spray

<b>Nozzle tip</b>	0.46 mm (0.018")
<b>Spray angle degrees</b>	65–80°
<b>Pressure at nozzle</b>	15–18 MPa (150–180 kg/cm <sup>2</sup> )

The product may be diluted in case of spray application. Thinner: water

### Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended, sawn wood:</b>	6 – 8	125 – 167	48 – 63
<b>Recommended, planed wood:</b>	8 – 12	83 – 125	32 – 48

### Cleaning of painting tools

Water and **JOTUN Penselrens** or water and a suitable cleaning agent.

### Thinner

Do not mix in oil additives.

### Conditions during application

Air and surface temperature must be above +5 °C during application.

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

Where condensation is possible, one should therefore finish the painting job well in advance.

- High humidity (RH%) significantly prolongs the drying time for waterborne products.
- Warm air can hold more moisture than cold air, and in case of temperature drop this can cause condensation.
- Stagnant air retards the drying, and can provide greater risk of condensation.
- Low temperature and condensation can provide inadequate film formation / curing.

The product contains effective agents against surface mould. In unfavorable drying and curing conditions, these can form a visible yellow compound in the surface. This is a surface phenomenon that will disappear after some time under the influence of light and UV rays. The phenomenon will not affect the product's effectiveness against surface fungi or otherwise impair the product's quality and durability.

## Drying times

Drying times deviate because of changes in temperature, air humidity, wind, absorption and film thickness.

The drying time is measured by stated values:

<b>Relative Humidity (RH)</b>	50 %	50 %	50 %
<b>Air temperature</b>	5 °C	15 °C	23 °C
<b>Substrate temperature</b>	5 °C	15 °C	23 °C

<b>Dust dry</b>	1.5 h	1 h	0.5 h
<b>Recoatible, minimum</b>	6 h	3 h	2 h

## Directions for use

The substrate must be clean, sound and dry.  
 Smooth sharp edges using emery/sand paper.

Substrate	Treatment
New / untreated timber:	New untreated or impregnated woodwork as well as exposed putty to be primed with 1 x <b>VISIR Oljegrunning</b> . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: Apply 3 coats <b>DEMIDEKK Infinity Details</b> on new planed woodwork and 2 coats on new sawn woodwork.
Vacuum and dip treated wood, as well as industrially applied substrates (containing wax or silicone):	Vacuum and dip treated wood, as well as industrially applied substrates (containing wax or silicone) should be degreased with methylated spirit. New untreated or impregnated woodwork as well as exposed putty to be primed with 1 x <b>VISIR Oljegrunning</b> . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: Apply 3 coats <b>DEMIDEKK Infinity Details</b> on new planed woodwork and 2 coats on new sawn woodwork.
Copper impregnated wood:	Pressure impregnated wood must be dry before treatment, ie the moisture in the wood should not exceed 20%. Then the surface must be washed well with water to remove surface salts before treatment. New untreated or impregnated woodwork as well as exposed putty to be primed with 1 x <b>VISIR Oljegrunning</b> . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: Apply 3 coats <b>DEMIDEKK Infinity Details</b> on new planed woodwork and 2 coats on new sawn woodwork.
Dirty surfaces /surfaces with surface mold:	Dirty surfaces with surface mold, discolorations and coatings are washed with <b>JOTUN 3-i-1 Kraftvask og Træ- og Murrens</b> diluted 1:15 with water. Any degraded, gray wood is removed by scraping / sanding. Rinse well with fresh water. New untreated or impregnated woodwork as well as exposed putty to be primed with 1 x <b>VISIR Oljegrunning</b> . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: Apply 3 coats <b>DEMIDEKK Infinity Details</b> on new planed woodwork and 2 coats on new sawn woodwork.
Previously treated wood:	Previously treated wood should be cleaned using <b>JOTUN 3-i-1 Kraftvask og Træ- og Murrens</b> diluted with water 1:10. Rinse well with fresh water. Sand glossy and hard surfaces. Remove loose stain/opaque stain and wood fibers by wire brush or scraping. New untreated or impregnated woodwork as well as exposed putty to be primed with 1 x <b>VISIR Oljegrunning</b> . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Topcoat: Apply 2 coats <b>DEMIDEKK Infinity Details</b> .
Gutters, fascias made of plastic and metal commonly used on buildings:	Clean with <b>JOTUN 3-i-1 Kraftvask og Træ- og Murrens</b> . Bare metal to be primed with two coats suitable primer. The primer must be brushed out thoroughly. Topcoat: Apply 2 coats <b>DEMIDEKK Infinity Details</b> .

### Storage

In storage and in transport keep the container frost free and upright.

### Disposal of waste

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

### Indoor environment / Emission

The product is recommended for outdoor use only.

### Contact information

Jotun A/S  
Box 2021  
NO-3202 Sandefjord  
Norway

Tel.: +47 33 45 70 00

### Disclaimer

# Technical Data Sheet

## DEMIDEKK Infinity Details



The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at [www.jotun.com](http://www.jotun.com).