

DRYGOLIN Color Expert

Product description

Type

Opaque wood protection for outdoor use with Longlasting Color Technology.



Features and benefits

DRYGOLIN Color Expert has Longlasting Color Technology which provides extreme color durability, superb color reproduction and long-lasting protection. The paint has a beautiful, muted, silky matte appearance, is especially effective against fungi and algae, and is self-cleaning.

Recommended use

To be used in combination with **VISIR Oljegrunning**, as part of a system treatment. To be applied to new, previously stained or painted woodwork, as well as impregnated. Also suitable as a topcoat for previously primed gutters, fascia's made of plastic and metal commonly use on buildings. Prime the metal with **QUICK Bengalack Grunning** or a suitable primer.



Oppbevares frostfritt



Vann/JOTUN Penselrens

Product data

Tinting	Bases must be tinted using Jotun Multicolor . Bases must not be used unless tinted (does not apply for white base).
Colours	White base may be used untinted as White.
Gloss level	25
Generic type	Acrylic paint.
Solids by volume	38 ± 2 volume%
Specific gravity	1.2
pH value	8.3
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 40 g/l VOC.

Application data

Remarks

To ensure long durability it is important to apply a sufficient amount on edges and planed surfaces, min. 3 coats (100 µm dry paint film). Sand down sharp edges. Remember to coat end grain. Can not be mixed with other paint products and do not mix in oil additives. The product shall not be thinned. Previous tar/mineral oil treatment and knots may cause discolouration/blistering of the topcoat. Linseed oil / oils in the substrate can cause blisters and flaking. Sun on semi-dry paint may cause skin drying and sun blisters. Painting on fire protected cladding may cause salt precipitation/flaking.

Bases must be tinted using **Jotun Multicolor**. Content of cans from different productions and different tinting systems may cause shade differences. Measures one can take to avoid colour differences:

- Mix different production numbers together. Stir well.
The production number can be found after the letters SZ or SV on the label in the front of the can.
- It is advantageous to use the same batch number within the same defined area.
Changing the can in the middle of the wall or confined area, increases the possibility of a visible colour difference.
- There may be colour differences of paint which are mixed on different tinting machines and / or at different times. Please be aware of this if you need to buy more paint / opaque stain / stain for the same project at a later time.
- If you notice any visible differences, contact your point of sale or Jotun Technical Service (tel. 33457530).

Application equipment / methods

Brush, roller or spray.

If applied by roller or spray, the surface must be brushed out immediately.
Use paint tools from the Jordan Ultimate series to achieve best results result.

Guiding data for airless spray

Nozzle tip	0.017–0.023"
Spray angle degrees	40–50°
Pressure at nozzle	15–18 MPa (150–180 kg/cm ²)

Cleaning of painting tools

Water and **JOTUN Penselrens** or water and a suitable cleaning agent.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended, sawn wood:	6 – 10	100 – 167	38 – 63
Recommended, planed wood:	10 – 12	83 – 100	32 – 38
Comments:	To ensure long durability it is important to apply a sufficient amount of paint on edges and planed surfaces, min. 3 coats (100 µm dry paint film).		

Conditions during application

Air and surface temperature must be above +5 °C during application.

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

- High humidity (RH%) significantly prolongs the drying time for waterborne products.
- Warm air can hold more moisture than cold air, and in case of temperature drop this can cause condensation.
- Stagnant air retards the drying, and can provide greater risk of condensation.
- Low temperature and condensation can provide inadequate film formation / curing.

Where condensation is possible, one should therefore finish the painting job well in advance.

The product contains effective agents against surface mould. In unfavorable drying and curing conditions, these can form a visible yellow compound in the surface. This is a surface phenomenon that will disappear after some time under the influence of light and UV rays. The phenomenon will not affect the product's effectiveness against surface fungi or otherwise impair the product's quality and durability.

Drying times

Drying times deviate because of changes in temperature, air humidity, wind, absorption and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %	50 %	50 %
Air temperature	23 °C	15 °C	5 °C
Substrate temperature	23 °C	15 °C	5 °C

Dust dry	0.5 h	1 h	1.5 h
Recoatable, minimum	2 h	3 h	10 h

TØRKEETID/ DRYING TIME	Støvtørr/ Dust dry/ Dammtorr Overmalbar/ Dry to recoat/ Intervall mellan strykningar	0t (h)	1t (h)	1,5t (h)	2t (h)	Ved ca. 50 % luftfuktighet/ At approx. 50% moisture
		+23 °C	+15 °C	+5 °C		
		0t (h)	2t (h)	3t (h)	6t (h)	
		+23 °C	+15 °C	+5 °C		

Directions for use

The substrate must be clean, sound and dry.
 For the best possible edge coverage, sand down sharp edges.

Substrate	Treatment
New woodwork:	Before or immediately after installation of new woodwork, treat with a brush coat of VISIR Oljegrunning . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 3 coats DRYGOLIN Color Expert on new planed woodwork and 2 coats on on new sawn woodwork.
Fresh wood left untreated for more than 4 weeks:	Should be cleaned using JOTUN 3-i-1 Kraftvask og Træ- og Murrens and brushed with a wire brush. Apply VISIR Oljegrunning to bare woodwork. The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 3 coats DRYGOLIN Color Expert on new planed woodwork and 2 coats on on new sawn woodwork.
Previously treated wood:	Should be cleaned using JOTUN 3-i-1 Kraftvask og Træ- og Murrens . Remove loose paint/stain and wood fibers by wire brush or scraping. Sand glossy and hard surfaces. Bare spots (from drybrushing/scraping) to be primed with VISIR Oljegrunning . The primer must be brushed out thoroughly. Apply 3-4 coats wet-on-wet to the end grains/cut surfaces. Apply 2 coats DRYGOLIN Color Expert .
Gutters, fascias made of plastic and metal commonly used on buildings:	Clean with JOTUN 3-i-1 Kraftvask og Træ- og Murrens . Bare metal to be primed with two coats suitable primer. Apply 2 coats DRYGOLIN Color Expert .

Maintenance

Wash the house with **JOTUN 3-i-1 Kraftvask og Træ- og Murrens** when necessary.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

BREEAM® NOR The product meets the requirements of the BREEAM® NOR for the VOC and the A20 list.

Green Building Standards

The declared product contributes to Green Building Standard credits by meeting the following specific requirements:

- Swan (2097 0003).

BREEAM® NOR (2016)

- Mat 01: Product-specific Type III EPD (ISO 14025, ISO 21930, EN 15804) for Scandinavia.
- Mat 01: The product Safety Data Sheet confirms that the product does not contain any substances on the Norwegian A20 list.

Additional information: Certificates and approvals may be available on request.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Product registration number: 4459127

Safety rules	
0-3	1993

Miscellaneous

Contact information

Technical Data Sheet

DRYGOLIN Color Expert



Jotun Danmark A/S
Jernet 6
6000 Kolding

Tel: +45 76 30 32 00
mail@jotun.dk

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Jotun office, please visit our website at www.jotun.com.