

Reveal Style E T

PRODUCT DESCRIPTION

Reveal Style E T is a range of TGIC-containing powder coatings providing a premium finish such as superior flow, high gloss and ultra matte non-sparkling finishes along with humidity and weathering resistance. The product meets the industry standard with regard to mechanical and chemical properties.

Application areas

This product is suitable for interior and exterior use.

Typical application areas:

- Automotive parts and accessories
- Air-conditioning units
- Electrical cabinets
- Exterior lighting fixtures
- Exterior trim
- Fences
- Outdoor industrial racking
- Satellite dish antennas
- Security cameras
- Steel doors
- Street and garden furniture
- Telecom and machinery enclosures

POWDER PROPERTIES

Property	Standard	Result
Specific gravity	Calculated	Typically 1.6±0.2 g/cm ³

Storage

Keep in a dry cool area. Maximum temperature 25 °C. Maximum relative humidity 60 %. If stored longer than 12 months a quality test must be performed.

APPLICATION

Pretreatment

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the pretreatment. For optimal results, it is recommended to follow the pretreatment supplier's instructions and recommendations.

Powder application

Curing schedule	Object temperature	Time
Reveal Style E0	200 °C	10 minutes

Recommended film thickness (µm): ≥50

Equipment

Suitable for Corona charging equipment. Please contact technical authority for Tribo use.

APPEARANCE

Colour Available in a wide range of colours.

Gloss EN ISO 2813 (60°)
Smooth:
Gloss 0-19
Gloss 90-100
Fine texture 0-9
Fine texture (Sahara) 7-17

Finish Smooth and fine textured finishes.

If the significant surface is too small or unsuitable for the gloss to be measured with the glossmeter, the gloss should be compared visually with the reference sample (from the same viewing angle).

PERFORMANCE

The technical data provided below are typical for this product when applied as follows:

Substrate Zinc-phosphated cold rolled steel panels
Substrate thickness (mm) 0.8
Film thickness (µm) 50-70

Typical values when tested.

Property	Standard	Result
Adhesion	ISO 2409	Cross-cut rating Gt0 (100 % adhesion)
Pencil hardness test *	ASTM D3363-05 (Derwent Graphic)	≥ H
Cupping test	ISO 1520	≥ 5 mm, no detachment
Impact resistance	ASTM D2794 (5/8 " ball) (inch-pounds, front only)	Gloss 0-19 (Ultra matte smooth and textured): ≥ 10 Gloss 90-100: 100/80 Fine texture (Sahara): 40/20
Resistance to neutral salt spray	ISO 9227 ISO 4628-2 ISO 4628-8	No blistering and maximum 2 mm corrosion creep from scratch after 504 hours
Resistance to humid atmospheres	ISO 6270-2	No blistering and maximum 2 mm corrosion creep from scratch after 500 hours
Accelerated weathering	ISO 16474-3	Cycle: 4 hours at 50 °C UV and 4 hours at 40 °C condensation. No chalking, excellent gloss retention and colour stability after 200 hours testing.

*Smooth, gloss 0-19

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.