

## JOTUN Industri LADY Pure Nature

### Product description

#### Type

Waterborne oil stain for interior use. Developed specifically for industrial application to the panel board.

#### Features and benefits

Gives a naturally beautiful finish that will enhance the woodwork. Contains light filter which effectively reduces yellowing.

#### Recommended use

For industrial application on interior pine panel.



### Product data

<b>Packaging size</b>	20 liter container (filling level 18 liter)
<b>Base availability</b>	Clear base
<b>Tinting</b>	Bases must be tinted using <b>Jotun Multicolor</b> .
<b>Colors</b>	LADY Pure Nature White The surface original colour, absorbency and number of coats affects the colour appearance.
<b>Gloss level</b>	02 Completely matt
<b>Generic type</b>	Alkyd oil diluted in water.
<b>Specific gravity</b>	1 - 1.15
<b>pH value</b>	8.5 to 8.8
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/e): 130 g/l. The product contains max 130 g/l VOC.

### Application data

**Substrate:** The substrate must be clean, sound and dry.

**Stirring:** Stir/mix thoroughly with a power agitator before application.

#### Application equipment / methods

Industrial application using brush machine or spray application.  
Contact your local Jotun representative for guidance and testing.

#### Cleaning of painting tools

Machinery and equipment must be cleaned with water.  
Use **JOTUN Penselrens** or **JOTUN Industri Kraftvask** as needed.

#### Thinner

Water.  
Can be diluted with water up to 10 %. The applied wet film thickness must be compensated for when diluting.

## Spreading rate and film thickness

### Spreading rate per coat (m<sup>2</sup>/liter)

**Recommended:** 30 – 35

The surface original colour, absorbency and number of coats affects the colour appearance. Final color must be checked against color reference. The stated spreading rate is an indication and must be adjusted if necessary.

## Conditions during application

Air, surface and paint temperature must be above +10 °C during application.  
Moisture content of woodwork max 18%.

## Drying times

When using drying zones and/or IR tubes: 4–10 min.  
Drying time depends on temperature, humidity and air speed in the drying zone. Adjust to the facility.

## Mounting and finishing treatment

The panel is mounted in accordance with the current norms and standards for carpentry.  
The substrate must be clean, sound and dry before further treatment.

When mounting:	Proper cleaning with clean hands and clean tools to avoid putting finger, dirt and grease marks on the panel is recommended. If necessary, use a mild synthetic detergent to wash away dirt and grease marks from the assembly work. Avoid using green soap and ammonia. Cut surfaces and bare wood can be treated with <b>LADY Pure Nature</b> from your local paint dealer.
Maintenance:	Stained surfaces must not be cleaned the first four weeks. If cleaning is necessary, the pH of the detergent must not exceed pH 9. <b>JOTUN Spesialvask for maling</b> is recommended. For daily cleaning the temperature of the wash water must be <40 °C. Avoid using green soap and ammonia.  Maintenance / repair - The panel can be stained with <b>LADY Pure Nature</b> or recoated with Jotun's interior paints adapted to wood.

## Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container frost free and upright.

## Disposal of waste

Liquid paint and washing water with paint residues must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

---

## Contact information

Jotun Sverige AB  
Box 151  
421 22 Västra Frölunda  
Tlf.: 031 69 63 00

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.