

Reveal Edge E U

PRODUCT DESCRIPTION

Reveal Edge is a range of bonded metallic powder coatings, developed with the designer in mind, to provide outstanding colours and finishes. The product can be recycled and will also meet industry standards in terms of mechanical and chemical resistance requirements.

Application areas

This product is suitable for interior and exterior use.

Typical application areas:

Outdoor furniture
Outdoor lighting
Park fixtures
Appliances

POWDER PROPERTIES

Property	Standard	Result
Specific gravity	Calculated	Typically 1.4±0.2 g/cm ³

Storage

Keep in a dry cool area. Maximum temperature 25 °C. Maximum relative humidity 60 %. If stored longer than 12 months a quality test must be performed.

APPLICATION

Pretreatment

The overall performance of the coating system is largely dependent on the nature of the substrate and the type and quality of the pretreatment. For optimal results, it is recommended to follow the pretreatment supplier's instructions and recommendations.

Powder application

Reveal Edge E0 U	200 °C	10 minutes
------------------	--------	------------

Recommended film thickness (µm): ≥60

Equipment

Suitable for Corona charging equipment.

APPEARANCE

Colour	Available in a wide variety of metallic colours and effects upon technical approval.
Gloss	Matt
Finish	Smooth

Metallic/special effect powder coatings are more sensitive to variations in application, it is important to consider recommendations given in our Application Guidelines for Metallic Powder Coatings.

PERFORMANCE

The technical data provided below are typical for this product when applied as follows:

Substrate Zinc phosphate cold rolled steel

Substrate thickness (mm) 0.8

Film thickness (µm) 60-80

Typical values when tested.

Property	Standard	Result
Adhesion	ISO 2409	Cross-cut rating Gt0 (100 % adhesion)
Pencil hardness test	ASTM D3363-05 (Derwent Graphic)	≥ H
Cupping test	ISO 1520	≥ 5 mm
Flexibility	ISO 1519	≤ 5 mm
Impact resistance	ASTM D2794 (5/8 " ball) (inch-pounds, front and reverse)	20/20
Resistance to neutral salt spray	ISO 9227 ISO 4628-2 ISO 4628-8	No blistering and maximum 2 mm corrosion creep from scribe after 504 hours
Resistance to humid atmospheres	ISO 6270-2 ISO 4628-2 ISO 4628-8	No blistering and maximum 2 mm corrosion creep from scribe after 504 hours
Accelerated weathering	ISO 16474-3	Cycle: 4 hours at 50 °C UV and 4 hours at 40 °C condensation. No chalking, excellent gloss retention and colour stability after 200 hours testing.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.