

## LADY Nordic Home

### Product description

#### Type

LADY Nordic Home is a premium paint formulated with advanced Nordic technology and high quality ingredients. Its elegant finish and rich beautiful colours provide excellent wet scrub resistance, mould and bacteria resistance to beautify and protect your home for many years. LADY Nordic Home delivers good indoor air climate.

#### Features and benefits

Elegant Finish: Deliver richer, thicker & smoother film with higher sheen

Rich Beautiful Colours: Deliver rich colour hues

EcoHealth: Free from harmful chemicals such as APEO, formaldehyde, heavy metals and has low volatile organic compound (VOC) and other hazardous matter emission. Deionized water formulation.

Low Odour: Low odour during and after painting.

Anti-Bacteria & Anti-Fungal: Prevent the spread of bacteria and growth of fungus indoors.

#### Recommended use

Ideal for interior surfaces.

#### Substrate

Putty, cement plaster, concrete, rendered block work etc.

### Product data

<b>Packaging size</b>	3 L
<b>Colours</b>	As per colour card and available in Jotun Multicolor tinting system (Interior range).
<b>Solids by volume</b>	37.5 ± 2 volume% Theoretical
<b>VOC comments</b>	< 1 g/l (Calculated)

### Application data

#### Remarks

Handle with care. Stir well before use.

#### The product can be applied by

Spray : Recommended.

Roller : Recommended.

Brush : Recommended.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.021-0.027"
<b>Spray angle degrees</b>	65-80°
<b>Pressure at nozzle</b>	140 - 190 kg/cm <sup>2</sup> (2100 psi)

## Spreading rate per coat

**Theoretical** 12 m<sup>2</sup>/l - 10 m<sup>2</sup>/l

Spreading rate depends on film thickness applied, type of texture, surface porosity, imperfections, temperature, wastage during painting etc.

## Recommended film thickness per coat

**Wet** 79 µm - 109 µm  
**Dry** 30 µm - 40 µm

Film thickness will vary and is calculated as average.

## Thinner

Water

## Dilution

The paint is ready to use after proper stirring. Mix no more than 5% water if thinning is required.

## Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

## Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

1. Recommended data given is, for recoating with the same generic type of paint.

2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied.

3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

### The drying time is measured by stated values:

**Relative Humidity (RH) 50 %**

<b>Substrate temperature</b>	10 °C	23 °C	40 °C
<b>Surface (touch) dry</b>	2 h	1 h	0.5 h
<b>Hard dry</b>	12 h	6 h	1 h
<b>Dry to over coat, minimum</b>	4 h	2 h	1 h

## Directions for use

### Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

### Recommended paint system

### Primer

LADY Primer : 1 coat

### Topcoat

LADY Nordic Home : 2 coats

### Remarks

Other systems may be specified, depending on area of use.

### Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

---

## Certificates

Finnish voluntary emission classification of building materials : M1  
French Regulations on VOC emissions : Class A+

---

## Tests

GB/T 9756: Synthetic resin emulsion coatings for interior wall  
GB 18582 : Limit of harmful substances of architectural wall coatings  
GB/T 21866: Test method and effect for antibacterial capability of paints film  
GB/T 1741: Test method for determining the resistance of paints film to mold

---

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.  
Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.