

Jotun Textotile Smooth

Product description

Type

Jotun Textotile Smooth is a high-build acrylic texture compound incorporating the multi-layer coating system to decorate and camouflage uneven walls.

Recommended use

For interior and exterior application.

Substrate

On concrete, masonry, plaster surfaces and brick work.

Product data

Packaging size	25 kg
Colours	White
Solids by volume	75 ± 2 volume%

Application data

Remarks

Handle with care. Stir well before use.

Application equipment / methods

Texture roller or Hopper Gun. Consult Jotun for additional information, as required.

Spreading rate per coat

Film thickness and spreading rate are varies depending on texture finish/pattern. General guideline is 0.8 - 1.4 m²/kg.

Thinner

Water

Conditions during application

The temperature of the substrate should be minimum 10 °C and at least 3 °C above the dew point of the air, measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Drying times

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

The given data must be considered as guidelines only. The actual drying time and time before recoating may be shorter or longer, depending on the ambient temperature, film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

1. Recommended data given is, for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The drying time is measured by stated values:

Relative Humidity (RH) 50 %

Substrate temperature 23 °C

Surface (touch) dry	3 h
Hard dry	24 h
Dry to over coat, minimum	24 h

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from dust, oil, grease, laitance etc. All traces of form release agents/curing agents must be removed. A light sanding with suitable abrasive material is recommended before application. Any resulting dust/loose particles must be removed.

Recommended paint system

Primer

Penguard Clear Sealer/ Jotashield Primer / Majestic Primer : 1 coat

Undercoat

Jotun Textotile

Topcoat

Majestic series/ Jotashield topcoats/ Pioneer 200 Gloss/ Pioneer 200 Matt : 2 coats

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.