

## BUTINOX Oljedekkbeis 2011-2023

### Product description

#### Type

Opaque oil stain for exterior woodwork.



#### Features and benefits

**BUTINOX Oljedekkbeis** provides an opaque subdued tree structure with good protection and durability. Rich consistency and good outflow. Can be applied below 0 °C.

#### Recommended use

To be used in combination with **BUTINOX Oljegrunning** or **BUTINOX Futura Grunning** as part of a system treatment. Recommended used on new primed, primed impregnated or previously stained or painted exterior woodwork.

Also suitable as a topcoat for previously primed gutters, fascia's made of plastic and metal commonly use on buildings. Bare metal to be first primed with **QUICK Bengalack Grunning**.

### Product data

<b>Packaging size</b>	3 (base 2,7) and 10 (base 9) liter.
<b>Base availability</b>	A, B, C, ochre, oxide red and yellow.
<b>Tinting</b>	Bases should be tinted before use.
<b>Colors</b>	White.
<b>Solids by volume</b>	54 ± 2 volume%
<b>Specific gravity</b>	1.22
<b>Particle size</b>	(White)
<b>Flash point</b>	Closed cup: 62°C (143.6°F)
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/e): 400 g/l. The product contains max 400 g/l VOC.

### Application data

#### Remarks

Stir well before use. Contents of tins with different production numbers should be mixed to avoid possible colour deviations.

Previously coated substrates containing mineral oils or tar may cause discolouration.

Surfaces previously treated with linseed oil or stains containing linseed oil may cause blistering when further opaque stain/paint coatings are applied.

#### Application equipment / methods

Roller + stain brush; or just stain brush.

#### Guiding data for airless spray

# Technical Data Sheet

## BUTINOX Oljedekkbeis 2011-2023



<b>Nozzle tip</b>	0.38-0.46 mm (0.015-0.018")
<b>Spray angle degrees</b>	65-80°
<b>Pressure at nozzle</b>	150-180 kg/cm <sup>2</sup>

Spraying: For professional application only.

### Cleaning of painting tools

Brush cleaner.

### Thinner

Shall not be thinned.

### Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended, sawn wood:</b>	5 - 8	125 - 200	68 - 108
<b>Recommended, planed wood:</b>	10 - 12	83 - 100	45 - 54

### Conditions during application

Moisture on semi-dry treatment may cause dull patches.  
Sun on semi-dry paint may cause skin drying and sun blisters.

### Drying times

The drying time is affected by temperature, air humidity and film thickness.  
Low temperature and high humidity prolongs the time before recoating.

<b>Relative Humidity (RH)</b>	50 %
<b>Air temperature</b>	23 °C
<b>Substrate temperature</b>	23 °C

<b>Recoatable, minimum</b>	24 hours
----------------------------	----------

### Directions for use

The substrate must be clean, sound and dry.

Substrate	Treatment
New woodwork:	Before or immediately after installation of new woodwork, treat with a brush coat of <b>BUTINOX Oljegrunning</b> . Apply 3-4 coats wet-on-wet to the end grains/cut surfaces.  Apply two coats <b>BUTINOX Oljedekkbeis</b> . Apply the product to 2-3 boards in the full length of the board at a time to reduce the risk of an uneven colour. Remember to coat end grain.

<p>Cladding which has been untreated longer than 3 weeks:</p>	<p>Wash with <b>BUTINOX Husvask og Kraftvask</b> (diluted with water 1:20). Rinse well with fresh water.                  Brush with a wire brush, scrape or grind with suitable tool. Remove loose wood fibers and loose paint.                  Apply <b>BUTINOX Sopp- og Algefjerner</b> in accordance with the user instructions.                  Apply <b>BUTINOX Oljegrunning</b>. Apply 3-4 coats wet-on-wet to the end grains/ cut surfaces.</p> <p>Apply two coats <b>BUTINOX Oljedekkbeis</b>. Apply the product to 2-3 boards in the full length of the board at a time to reduce the risk of an uneven colour. Remember to coat end grain.</p>
<p>Bare and weathered woodwork:</p>	<p>Wash with <b>BUTINOX Husvask og Kraftvask</b> (diluted with water 1:20). Rinse well with fresh water.                  Brush with a wire brush, scrape or grind with suitable tool. Remove loose wood fibers.                  Apply <b>BUTINOX Sopp- og Algefjerner</b> in accordance with the user instructions.                  Apply <b>BUTINOX Oljegrunning</b>. Apply 3-4 coats wet-on-wet to the end grains/ cut surfaces.</p> <p>Apply two coats <b>BUTINOX Oljedekkbeis</b>. Remember to coat end grain.</p>
<p>Previously treated and intact surfaces:</p>	<p>Wash with <b>BUTINOX Husvask og Kraftvask</b> (diluted with water 1:10). Rinse well with fresh water.                  Apply <b>BUTINOX Sopp- og Algefjerner</b> in accordance with the user instructions.</p> <p>Apply 1-2 coats <b>BUTINOX Oljedekkbeis</b>. Apply the product to 2-3 boards in the full length of the board at a time to reduce the risk of an uneven colour. Remember to coat end grain.</p>
<p>Old weathered stain, opaque stain or paint:</p>	<p>Wash with <b>BUTINOX Husvask og Kraftvask</b> (diluted with water 1:10). Rinse well with fresh water.                  Brush with a wire brush, scrape or grind with suitable tool. Remove loose wood fibers and loose paint.                  Apply <b>BUTINOX Sopp- og Algefjerner</b> in accordance with the user instructions.                  Bare wood to be primed with <b>BUTINOX Futura Grunning</b>.</p> <p>Apply two coats <b>BUTINOX Oljedekkbeis</b>. Apply the product to 2-3 boards in the full length of the board at a time to reduce the risk of an uneven colour. Remember to coat end grain. Apply two coats</p>

### Management, Operation and Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

### Storage

Can be stored and used in freezing temperatures.

### Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

---

## Miscellaneous

### Contact information

Jotun Sverige AB  
Box 151  
421 22 Västra Frölunda  
Tlf.: +46 031 69 63 00

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Jotun Sverige AB for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.