

JOTUN Premium mur topcoat

Product description

Type

Permeable, water repellent, silicone emulsion topcoat for outdoor use.

Features and benefits

Using non-fading mineral pigments and fillers will provide excellent weather resistance. Contains effective film conserving agent that counteract mould growth.

JOTUN Premium mur maling is classified as diffusion open paint according to EN ISO 7783-2/DIN 52615 (Sd < 0,14 m) and in class for low water absorption according to EN ISO 1062-3 ($W_{24} < 0,1 \text{ kg/m}^2\text{h}^{0,5}$)

Recommended use

Suitable for all types of plaster and other mineral surfaces, both untreated and previously painted. The product is recommended for outdoor use only.

Product data

Packaging size	0,75 L (contents 0,68 L), 3 L (content 2.7 L) and 10 L (content 9 L)
Base availability	A, C and Light Grey, Medium Grey, Dark Grey. Bases must not be used unless tinted (does not apply for grey bases).
Tinting	Can only be used in Jotun Multicolor tinting machines. Must be tinted using Jotun Multicolor . For masonry colours in swatches for exterior products, based on mineral tinters. Grey bases can be tinted on any Jotun Multicolor tinting machine, A- and C-base to be tinted on machines with special mineral tinters.
Colors	Hvit, Isgrå 7356 (Light grey base), Idyll 4456 (Medium grey base) and Kveldsskygge 4455 (Dark grey base). Colours according to Jotun's Masonry Swatches and Jotun's Swatches for Exterior Products.
Gloss level	Matt
Generic type	Silicone emulsion paint
Solids by volume	43,2 ± 2 volume%
Specific gravity	1,54 (A-base)
Flash point	
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/c): 40 g/l. The product contains max 40 g/l VOC.

Application data

Remarks

Stir well. Contents of tins with different production numbers should be mixed. During unfavorable drying conditions (high humidity, fog, rain, low temperatures), glossy, lightly sticky streaks may occur on the paint film. The stripes consist of water-soluble substances, and will disappear by repeated or heavy rainfall. The permeable and protective properties of the paint will not deteriorate if striping occurs.

Application equipment / methods

Brush, roller or spray. Apply rich and evenly.

Guiding data for airless spray

Nozzle tip	0.38 mm (0.015")
Spray angle degrees	40° - 80°

Technical Data Sheet

JOTUN Premium mur topcoat



Pressure at nozzle Min. 15 MPa (Min. 150 kg/cm²)

Cleaning of painting tools

Water and **JOTUN Penselrens**.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Recommended film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	6 - 9	111 - 167	48 - 72

Dilution

Do not mix in oil additives.

Conditions during application

The air and surface temperature must be above + 5 °C.

Drying times

The drying time depends on the surface temperature (min. +5 °C), absorption, humidity and air circulation.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %	50 %
Air temperature	10 °C	23 °C
Substrate temperature	10 °C	23 °C

Dust dry	2 h	1 h
Paintable	20 h	10 h

Directions for use

Surface preparation

The substrate must be clean, sound and dry. New plaster should be applied according to current standards. Loose paint and plaster, and possible lime wash must be removed. Fungus, soot and other contamination must be removed, using **JOTUN 2i1 Kraftvask og soppfjerner** / **JOTUN 2i1 Kraftvask och mögeldesinfektion** / **JOTUN 2i1 Kraftvask og Træ og Murrens** - window panels should be covered. Rinse with clean water. New plaster should be allowed to cure for minimum 4 weeks before treatment. Any constructional weaknesses must be repaired before painting.

Primer

Untreated brick / plaster must be primed with JOTUN Premium mur grunning.

Undercoat

Smoothing of small cracks and irregularities: **JOTUN Premium mur filler**.
When smoothing of structural irregularities in the substrate and bridging of cracks up to 0.5 mm is required, **JOTUN Premium mur filler** should be used as intermediate coat.
Must always be overpainted with **JOTUN Premium mur maling**.

Topcoat

Technical Data Sheet

JOTUN Premium mur topcoat



2 x **JOTUN Premium mur topcoat**. If **JOTUN Premium mur filler**, 1 x of **JOTUN Premium mur maling** is sufficient.

Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB-numbers:

45967736, 45970358, 45970396, 45967766, 45970453, 45970426, 45967740, 45970362, 45970400, 45970381, 45970415, 45967774, 45970464, 45970434, 45967785, 45970472, 45970445

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (Eng) version will prevail.